



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
42
 Component
Compressor
 Fluid
PETRO CANADA SENTRON LD 3000 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0111894	PCA0111991	PCA0111920
Sample Date		Client Info		02 May 2024	02 Apr 2024	05 Mar 2024
Machine Age	hrs	Client Info		98190	97500	97500
Oil Age	hrs	Client Info		690	283	3347
Filter Age	hrs	Client Info		690	283	3347
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	5	6	2
Chromium	ppm	ASTM D5185m	>10	<1	<1	0
Nickel	ppm	ASTM D5185m		<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	<1	<1
Aluminum	ppm	ASTM D5185m	>25	<1	1	2
Lead	ppm	ASTM D5185m	>25	5	6	5
Copper	ppm	ASTM D5185m	>50	15	16	13
Tin	ppm	ASTM D5185m	>15	7	7	7
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION


There is no indication of any contamination in the component.

Silicon	ppm	ASTM D5185m	>25	2	2	1
Potassium	ppm	ASTM D5185m	>20	8	5	4
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	0	3
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	1	0	0	0
Molybdenum	ppm	ASTM D5185m	2	3	3	2
Manganese	ppm	ASTM D5185m	1	<1	<1	<1
Magnesium	ppm	ASTM D5185m	5	16	19	18
Calcium	ppm	ASTM D5185m	1220	1321	1345	1319
Phosphorus	ppm	ASTM D5185m	298	291	309	280
Zinc	ppm	ASTM D5185m	350	356	353	357
Sulfur	ppm	ASTM D5185m	1995	2824	2823	2426
Acid Number (AN)	mg KOH/g	ASTM D8045	0.86	0.923	0.885	0.805
Visc @ 40°C	cSt	ASTM D445	124.3	124	121	121



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0111894 **Received** : 09 May 2024
Lab Number : 06174017 **Tested** : 12 May 2024
Unique Number : 11020070 **Diagnosed** : 12 May 2024 - Don Baldrige
Test Package : MOB 2 (Additional Tests: FuelDilution, TBN)

ENERVEST OPERATING - HAYS BOOSTER
 1705 BREAKS PARK ROAD
 HAYS1, VA
 US 24256
 Contact: Service Manager

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: