



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id

44

Component

Natural Gas Engine

Fluid

PETRO CANADA SENTRON LD 3000 (--- GAL)

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0112038	PCA0117150	PCA0112035
Sample Date		Client Info		01 May 2024	01 Apr 2024	04 Mar 2024
Machine Age	hrs	Client Info		105615	104911	104243
Oil Age	hrs	Client Info		1110	406	1831
Filter Age	hrs	Client Info		1110	406	1831
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	2	2	8
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	<1	1	1
Lead	ppm	ASTM D5185m	>30	1	1	2
Copper	ppm	ASTM D5185m	>35	2	<1	<1
Tin	ppm	ASTM D5185m	>4	<1	1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













Fuel content negligible. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	2	1	2
Potassium	ppm	ASTM D5185m	>20	3	2	<1
Fuel	%	ASTM D3524	>4.0	0.1	0.1	0.3
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	9.8	5.4	5.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.8	14.1	15.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	0	2
Boron	ppm	ASTM D5185m	5	2	8	<1
Barium	ppm	ASTM D5185m	1	0	0	0
Molybdenum	ppm	ASTM D5185m	2	5	5	<1
Manganese	ppm	ASTM D5185m	1	<1	<1	<1
Magnesium	ppm	ASTM D5185m	5	19	18	17
Calcium	ppm	ASTM D5185m	1220	1316	1278	1322
Phosphorus	ppm	ASTM D5185m	298	311	310	289
Zinc	ppm	ASTM D5185m	350	374	353	373
Sulfur	ppm	ASTM D5185m	1995	2418	2616	2310
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.9	9.4	9.6
Acid Number (AN)	mg KOH/g	ASTM D8045	0.86	1.72	0.91	▲ 2.41
Base Number (BN)	mg KOH/g	ASTM D2896	3.9	1.82	3.31	▲ 1.72
Visc @ 100°C	cSt	ASTM D445	13.7	13.7	13.3	13.7



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0112038 **Received** : 09 May 2024
Lab Number : 06174053 **Tested** : 15 May 2024
Unique Number : 11020106 **Diagnosed** : 15 May 2024 - Wes Davis
Test Package : MOB 2 (Additional Tests: FuelDilution, PercentFuel)

ENERVEST OPERATING - WATKINS
 3896 SUNSET HOLLOW ROAD
 GRUNDY, VA
 US 24614
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: