

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Area

Store 5 - Cross Lanes JOHN DEERE 160P 1FF160PAJPF000099

Swing Drive

JOHN DEERE GL-5 80W90 (2 GAL)

| JOHN DEERE GL-5 80W90 (2 G | AL) | | | | | | |
|---|------------------|--------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | LEC0031412 | | |
| | Sample Date | | Client Info | | 07 May 2024 | | |
| | Machine Age | hrs | Client Info | | 428 | | |
| | Oil Age | hrs | Client Info | | 428 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | PQ | | ASTM D8184 | | 40 | | |
| | Iron | ppm | ASTM D5185m | >151 | 31 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | | <1 | | |
| | Nickel | ppm | ASTM D5185m | >10 | <1 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >21 | <1 | | |
| | Lead | ppm | ASTM D5185m | >51 | <1 | | |
| | Copper | ppm | ASTM D5185m | >51 | 1 | | |
| | Tin | ppm | ASTM D5185m | >10 | 1 | | |
| | Vanadium | ppm | ASTM D5185m | | <1 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >31 | 19 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | | 4 | | |
| | Water | | WC Method | >0.1 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.1 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | >51 | 0 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | | 77 | | |
| | Barium | ppm | ASTM D5185m | | <1 | | |
| | Molybdenum | ppm | ASTM D5185m | | <1 | | |
| | Manganese | ppm | ASTM D5185m | | 2 | | |
| | Magnesium | ppm | ASTM D5185m | | 4 | | |
| | Calcium | ppm | ASTM D5185m | | 108 | | |
| | Phosphorus | ppm | ASTM D5185m | | 531 | | |
| | Zinc | ppm | ASTM D5185m | | 43 | | |
| | Sulfur | ppm | ASTM D5185m | | 16507 | | |
| | Visc @ 40°C | cSt | ASTM D445 | | 180 | | |







Certificate L2367

Laboratory Sample No.

Lab Number : 06174127 Unique Number : 11020180

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0031412

Test Package : CONST (Additional Tests: PQ)

Received : 09 May 2024 **Tested** Diagnosed

: 10 May 2024

: 10 May 2024 - Wes Davis

US 45750-9765 Contact: LEANNE KENDALL KendalLeanne@lec1.com

LESLIE EQUIPMENT COMPANY

T:

105 TENNIS CENTER DR.

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (740)373-5570

MARIETTA, OH