

Area



## [715058 ALTA RENTS] VOLVO A25G 753028 ponent

**Rear Axle** 

## VOLVO PREMIUM GEAR OIL 85W-140 GL-5 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP449617		
	Sample Date		Client Info		06 May 2024		
	Machine Age	hrs	Client Info		369		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR				000	100		
WEAN	Iron	ppm	ASTM D5185m		108		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium Silver	ppm	ASTM D5185m ASTM D5185m		0		
		ppm		. 20	0		
	Aluminum Lead	ppm	ASTM D5185m ASTM D5185m		0 <1		
	Copper	ppm	ASTM D5185m		13		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	>20	0		
	White Metal	ppm scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
		Scala	visuai				
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	3		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	5		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
	Boron	ppm	ASTM D5185m	111	319		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		4		
	Molybdenum	ppm	ASTM D5185m		12		
	Manganese	ppm	ASTM D5185m		12		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		90		
	Phosphorus	ppm	ASTM D5185m		1482		
	Zinc	ppm	ASTM D5185m		54		
	Sulfur	ppm	ASTM D5185m		28705		


Visc @ 40°C


cSt


ASTM D445 333

Contact/Location: Robert LaPlante - VOLVO0096

106







Contact/Location: Robert LaPlante - VOLVO0096 Page 2 of 2