

ISA9387 WM] Machine Id VOLVO L90H 626204 Component Front Axle Fluid VOLVO WB 102 (--- GAL)

## RECOMMENDATION

Resample at the next service interval to monitor.

## **WEAR**

All component wear rates are normal.

## CONTAMINATION

There is no indication of any contamination in the oil.

## FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP430339		
Sample Date		Client Info		07 May 2024		
Machine Age	hrs	Client Info		1435		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
Iron	ppm	ASTM D5185m	>300	64		
Chromium	ppm	ASTM D5185m	>10	2		
Nickel	ppm	ASTM D5185m	>4	- <1		
Titanium	ppm	ASTM D5185m	~7	0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>15	<1		
Lead	ppm	ASTM D5185m	>4	2		
Copper	ppm	ASTM D5185m	>200	- <1		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m	210	0		
White Metal	scalar	*Visual	NONE			
Yellow Metal			NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Yellow Metal Silicon			-	-		
	scalar	*Visual	NONE	NONE		
Silicon	scalar ppm	*Visual ASTM D5185m	NONE	NONE 21		
Silicon Potassium	scalar ppm	*Visual ASTM D5185m ASTM D5185m	NONE >75 >20	NONE 21 <1		
Silicon Potassium Water	scalar ppm ppm	*Visual ASTM D5185m ASTM D5185m WC Method	NONE >75 >20 >0.2	NONE 21 <1 NEG		
Silicon Potassium Water Silt	scalar ppm ppm scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual	NONE >75 >20 >0.2 NONE	NONE 21 <1 NEG NONE	  	  
Silicon Potassium Water Silt Debris	scalar ppm ppm scalar scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual	NONE >75 >20 >0.2 NONE NONE	NONE 21 <1 NEG NONE NONE	  	  
Silicon Potassium Water Silt Debris Sand/Dirt	scalar ppm ppm scalar scalar scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual	NONE >75 >20 >0.2 NONE NONE NONE	NONE 21 <1 NEG NONE NONE NONE		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance	scalar ppm ppm scalar scalar scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual	NONE >75 >20 >0.2 NONE NONE NONE NORML	NONE 21 <1 NEG NONE NONE NONE NORML		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor	scalar ppm ppm scalar scalar scalar scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NONE NORML NORML		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water	scalar ppm ppm scalar scalar scalar scalar scalar scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual *Visual	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORE NORML NORML NEG		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium	scalar ppm ppm scalar scalar scalar scalar scalar scalar	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual *Visual ASTM D5185m	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORE NORML NEG 11		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron	scalar ppm scalar scalar scalar scalar scalar scalar scalar ppm	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual *Visual *Visual ASTM D5185m	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORML NORML NEG 11 129		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium	scalar ppm ppm scalar scalar scalar scalar scalar scalar ppm	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual ASTM D5185m ASTM D5185m	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORML NORML NEG 11 129 <1		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Molybdenum	scalar ppm scalar scalar scalar scalar scalar scalar ppm ppm	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual ASTM D5185m ASTM D5185m ASTM D5185m	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORML NORML NEG 11 129 <1 10		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Molybdenum Manganese	scalar ppm scalar scalar scalar scalar scalar scalar ppm ppm ppm	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORML NORML NEG 11 129 <1 10 7		
Silicon Potassium Water Silt Debris Sand/Dirt Appearance Odor Emulsified Water Sodium Boron Barium Molybdenum Manganese Magnesium	scalar ppm scalar scalar scalar scalar scalar scalar ppm ppm ppm ppm	*Visual ASTM D5185m ASTM D5185m WC Method *Visual *Visual *Visual *Visual *Visual ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	NONE >75 >20 >0.2 NONE NONE NONE NORML NORML	NONE 21 <1 NEG NONE NONE NORML NORML NEG 11 129 <1 10 7 12		

Sulfur

Visc @ 40°C

ppm


cSt


ASTM D5185m ASTM D445 55

Contact/Location: JIM STRIGLE - VOLVO0142

4731

40.3





Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 ALTA EQUIPMENT Sample No. Received 5985 COURT STREET ROAD : VCP430339 :09 May 2024 Lab Number : 06174263 Tested SYRACUSE, NY : 10 May 2024 Diagnosed Unique Number : 11020316 : 10 May 2024 - Wes Davis US 13206 Test Package : MOB 1 Contact: JIM STRIGLE Certificate L2367 JIM.STRIGLE@ALTG.COM To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (315)437-2611 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (315)434-9471

Contact/Location: JIM STRIGLE - VOLVO0142 Page 2 of 2