WEAR CONTAMINATION FLUID CONDITION

ABNORMAL NORMAL NORMAL



Wachine Id VOLVO A25G 742179

Brake

{not provided} (--- GAL)

	MEN		 $\sim$ LI
$\mathbf{H}$	икиек		
115		1VF	

No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0003021		
Sample Date		Client Info		29 Apr 2024		
Machine Age	hrs	Client Info		2183		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Filter Changed		Client Info		N/A		
Sample Status				ABNORMAL		
Iron	ppm	ASTM D5185m	>50	13		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>10	1		

## **WEAR**

The copper level is abnormal. All other component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	13	 
Chromium	ppm	ASTM D5185m	>20	0	 
Nickel	ppm	ASTM D5185m	>10	1	 
Titanium	ppm	ASTM D5185m		0	 
Silver	ppm	ASTM D5185m		0	 
Aluminum	ppm	ASTM D5185m	>30	1	 
Lead	ppm	ASTM D5185m	>50	5	 
Copper	ppm	ASTM D5185m	>200	<b>△</b> 320	 
Tin	ppm	ASTM D5185m	>20	0	 
Vanadium	ppm	ASTM D5185m		0	 
White Metal	scalar	*Visual	NONE	NONE	 
Yellow Metal	scalar	*Visual	NONE	NONE	 
0:1:		AOTA DE LOS			 
Silicon	ppm	ASTM D5185m	>50	31	 
Potassium	ppm	ASTM D5185m	>20	1	 
Water		MC Mothod	×0.2	NEC	

## **CONTAMINATION**


There is no indication of any contamination in the fluid.

	vvalei		WC Method	>0.2	NEG	 
	Silt	scalar	*Visual	NONE	NONE	 
	Debris	scalar	*Visual	NONE	NONE	 
	Sand/Dirt	scalar	*Visual	NONE	NONE	 
_	Appearance	scalar	*Visual	NORML	NORML	 
	Odor	scalar	*Visual	NORML	NORML	 
	Emulsified Water	scalar	*Visual	>0.2	NEG	 
	Sodium	ppm	ASTM D5185m		7	 
	Boron	ppm	ASTM D5185m		133	 

## **FLUID CONDITION**

The condition of the fluid is acceptable for the time in service.

	Oddi	Scalai	VISUAI	NONIVIL	NONIVIL	 
	Emulsified Water	scalar	*Visual	>0.2	NEG	 
	Sodium	ppm	ASTM D5185m		7	 
	Boron	ppm	ASTM D5185m		133	 
	Barium	ppm	ASTM D5185m		0	 
	Molybdenum	ppm	ASTM D5185m		0	 
	Manganese	ppm	ASTM D5185m		2	 
	Magnesium	ppm	ASTM D5185m		11	 
	Calcium	ppm	ASTM D5185m		3820	 
	Phosphorus	ppm	ASTM D5185m		1359	 
	Zinc	ppm	ASTM D5185m		1737	 
	Sulfur	ppm	ASTM D5185m		5723	 
	Visc @ 40°C	cSt	ASTM D445		39.9	 
			_			 







Laboratory Sample No.

Lab Number : 06174306 Unique Number : 11020359

: ASC0003021 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 09 May 2024 **Tested** : 10 May 2024 Diagnosed

: 13 May 2024 - Don Baldridge

160 - ASCENDUM MACHINERY INC - MILLS RIVER 215 FANNING FIELDS RD

MILLS RIVER, NC US 28759

Contact: CORY PENLAND

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. cory.penland@ascendummachinery.com T: (828)687-0620

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)