WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



[UNITED RENTALS] Wachine Id VOLVO A25G 742179 Component

Front Right Final Drive [Fluid for provided] (--- GAL)


{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		ASC0003013	VCP296189	
	Sample Date		Client Info		29 Apr 2024	10 Mar 2021	
	Machine Age	hrs	Client Info		2183	1743	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		N/A	Changed	
	Filter Changed		Client Info		N/A	Not Changd	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>900	88	442	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	1	9	
	Nickel	ppm	ASTM D5185m		<1	5	
	Titanium	ppm	ASTM D5185m		0	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>30	0	<1	
	Lead	ppm	ASTM D5185m	>50	0	0	
	Copper	ppm	ASTM D5185m	>150	6	24	
	Tin	ppm	ASTM D5185m	>20	0	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	3	4	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1	0	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	MODER	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3	4	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		272	186	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		<1	4	
	Manganese	ppm	ASTM D5185m		4	21	
	Magnesium	ppm	ASTM D5185m		0	0	
	Calcium	ppm	ASTM D5185m		46	37	
	Phosphorus	ppm	ASTM D5185m		2172	1511	
	Zinc	ppm	ASTM D5185m		24	16	
	Sulfur	ppm	ASTM D5185m		31414	22204	


Visc @ 40°C


64.5


52.6

ASTM D445











Certificate L2367

Laboratory Sample No.

: ASC0003013 Lab Number : 06174309 Unique Number : 11020362 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 09 May 2024 **Tested** : 10 May 2024

Diagnosed : 10 May 2024 - Wes Davis

160 - ASCENDUM MACHINERY INC - MILLS RIVER 215 FANNING FIELDS RD

MILLS RIVER, NC US 28759

Contact: CORY PENLAND cory.penland@ascendummachinery.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (828)687-0620 F: (828)687-0622

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: CORY PENLAND - VOLVO1672