WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Area


[W02008273] Machine Id VOLVO L70H 622433





TRANSAXLE OIL SAE 75W80 (8 GAL)

TRANSAXLE OIL SAE 75W80 (8 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. (Customer Sample Comment: W02008273)	Sample Number		Client Info		ML0000994		
	Sample Date		Client Info		07 May 2024		
	Machine Age	hrs	Client Info		11739		
	Oil Age	hrs	Client Info		2000		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	84		
	Chromium	ppm	ASTM D5185m		2		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		- <1		
	Titanium	ppm	ASTM D5185m	,	<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m	>120	11		
	Tin	ppm	ASTM D5185m	>20	1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION							
CONTAMINATION	Silicon	ppm	ASTM D5185m		16		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		3		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	LIGHT		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance Odor	scalar	*Visual	NORML NORML	NORML NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
	Linuidilica Water		····				
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		142		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	25	2		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m		16		
	Calcium	ppm	ASTM D5185m		3535		
	Phosphorus	ppm	ASTM D5185m		1213		
	Zinc	ppm	ASTM D5185m		1407		
	Sulfur	ppm	ASTM D5185m		8462		
	Visc @ 40°C	cSt	ASTM D445	48	48.7		











Certificate L2367

Laboratory Sample No.

: ML0000994 Lab Number : 06174360 Unique Number : 11020413 Test Package : CONST To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 09 May 2024 **Tested** : 10 May 2024

Diagnosed : 13 May 2024 - Don Baldridge **WILLIAM HAZEL** PO BOX 600 CHANTILLY, VA US 20153

Contact: SERVICE MANAGER jimmy_elswick@wahazel.com T: (703)378-8300

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: