



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

ELEANOR G MCDONALD

Machine Id

[ELEANOR G MCDONALD] 006 552824-6

Component

Starboard Reduction Gear

Fluid

CHEVRON MEROPA 320 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0068226	MW0065843	MW0065702
Sample Date		Client Info		01 May 2024	01 Apr 2024	05 Mar 2024
Machine Age	hrs	Client Info		181334	180633	180024
Oil Age	hrs	Client Info		14025	13324	12715
Filter Age	hrs	Client Info		14025	0	12715
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	None	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	53	51	48
Chromium	ppm	ASTM D5185m	>10	0	<1	0
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	0	<1
Lead	ppm	ASTM D5185m	>100	2	<1	2
Copper	ppm	ASTM D5185m	>50	3	5	4
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	4	3	4
Potassium	ppm	ASTM D5185m	>20	2	0	2
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		37	33	33
Boron	ppm	ASTM D5185m	20	10	16	13
Barium	ppm	ASTM D5185m		0	<1	<1
Molybdenum	ppm	ASTM D5185m	0	0	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		<1	<1	2
Calcium	ppm	ASTM D5185m	25	22	63	50
Phosphorus	ppm	ASTM D5185m	235	309	295	295
Zinc	ppm	ASTM D5185m		3	12	8
Sulfur	ppm	ASTM D5185m		7007	6813	6654
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	0.49	0.50	0.53
Visc @ 40°C	cSt	ASTM D445	304	317	314	315



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0068226

Lab Number : 06174693

Unique Number : 11020746

Test Package : MAR 2

Received : 09 May 2024

Tested : 10 May 2024

Diagnosed : 10 May 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: ANTHONY VAN CURA

anthony.vancura@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)