WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

JOHN DEERE 310SL 1T0310SLAKF356390

Front Right Final Drive

JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

JOHN DEERE HY-GARD HYD/TRANS (GAL))						
RECOMMENDATION Resample at the next service interval to monitor.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		JR0207794		
	Sample Date		Client Info		03 May 2024		
	Machine Age	hrs	Client Info		1528		
	Oil Age	hrs	Client Info		1528		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	DO.		ACTA DOLOA	1050			
WEAR	PQ		ASTM D8184		24		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		293		
	Chromium	ppm	ASTM D5185m		6		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	40	0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		2		
	Vanadium	ppm	ASTM D5185m	>10	<1 0		
		ppm	ASTM D5185m	NONE			
	White Metal Yellow Metal	scalar	*Visual *Visual	NONE	NONE		
	reliow Metal	scalar	visuai	INOINE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	15		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	11		
	Boron	ppm	ASTM D5185m		121		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m	145	14		
	Calcium	ppm	ASTM D5185m		3577		
	Phosphorus	ppm	ASTM D5185m		1177		
	Zinc	ppm	ASTM D5185m		1434		
	Sulfur	ppm	ASTM D5185m		4301		
	Visc @ 40°C	cSt	ASTM D445	57.0	54.2		
Report Id: VANASH [WLISCAR] 06174757 (Generated: 05/13/2024 13:49:07) Rev: 1	VISC @ 40 C	CSI	ASTIVI D443		/Location: Ba	andy Marron	\/





Laboratory Sample No.

: JR0207794 Lab Number : 06174757 Unique Number : 11020810

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 09 May 2024 Diagnosed

: 10 May 2024 : 13 May 2024 - Sean Felton

JRE - ASHEVILLE 101 BRUCE DRIVE ASHEVILLE, NC US 28806 Contact: Randy Warren

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

randy.warren@jamesriverequipment.com T: (528)667-0176

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (828)667-4865