

Machine Id **KOMATSU 43006** Component **Diesel Engine**


KENDALL 15W40 (--- QTS)

KENDALL 131140 (Q13)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WC0867767		
	Sample Date		Client Info		25 Apr 2024		
	Machine Age	hrs	Client Info		1399		
	Oil Age	hrs	Client Info		367		
	Filter Age	hrs	Client Info		367		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron		ASTM D5185m	×100	0		
WEAN	Chromium	ppm	ASTM D5185m		8 <1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>4	84		
	Silver	ppm	ASTM D5185m	. 2	0		
	Aluminum	ppm	ASTM D5185m				
		ppm			2		
	Lead	ppm	ASTM D5185m		<1		
	Copper Tin	ppm	ASTM D5185m		2		
		ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	4		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	9.2		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	22.0		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium		ASTM D5185m		3		
	Boron	ppm	ASTM D5185m	63	3 144		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm ppm	ASTM D5185m ASTM D5185m		37		
	Manganese		ASTM D5185m	0.4	0		
	Magnesium	ppm	ASTM D5185m	277	480		
	-	ppm					
	Calcium	ppm	ASTM D5185m		1818		
	Phosphorus	ppm	ASTM D5185m		1108		
	Zinc	ppm	ASTM D5185m		1269		
	Sulfur	ppm	ASTM D5185m		4095		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	17.5		
	Base Number (BN)	mg KOH/g	ASTM D2896		7.6		

Visc @ 100°C cSt

ASTM D445

14.2



GREENEVILLE OIL & PETROLEUM INC Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WC0867767 Received 860 WEST ANDREW JOHNSON HWY :09 May 2024 Lab Number : 06174908 Tested : 10 May 2024 GREENEVILLE, TN Unique Number : 11020961 Diagnosed : 10 May 2024 - Wes Davis US 37745 Test Package : FLEET Contact: SHOP Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. shop@burkhartenterprises.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Т: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Contact/Location: SHOP ? - GREGRETN Page 2 of 2