



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

(P633833)

Machine Id

3761C

Component

Natural Gas Engine

Fluid

PETRO CANADA DURON GEO LD 15W40 (40 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0101769	GFL0101798	GFL0090074
Sample Date		Client Info		30 Apr 2024	23 Feb 2024	02 Nov 2023
Machine Age	hrs	Client Info		19701	19100	18600
Oil Age	hrs	Client Info		601	600	600
Filter Age	hrs	Client Info		601	600	600
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	13	12	21
Chromium	ppm	ASTM D5185m	>4	1	<1	2
Nickel	ppm	ASTM D5185m	>2	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	3	2	1
Lead	ppm	ASTM D5185m	>30	<1	0	<1
Copper	ppm	ASTM D5185m	>35	<1	<1	<1
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>+100	6	4	22
Potassium	ppm	ASTM D5185m	>20	2	2	0
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.1	9.5	10.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.2	21.0	17.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		8	2	6
Boron	ppm	ASTM D5185m	50	34	20	17
Barium	ppm	ASTM D5185m	5	0	8	<1
Molybdenum	ppm	ASTM D5185m	50	75	54	57
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	560	797	562	725
Calcium	ppm	ASTM D5185m	1510	2270	1540	1459
Phosphorus	ppm	ASTM D5185m	780	1164	827	814
Zinc	ppm	ASTM D5185m	870	1365	975	1084
Sulfur	ppm	ASTM D5185m	2040	3548	2602	2538
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8	17.5	16.9
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	7.3	6.7	9.5
Visc @ 100°C	cSt	ASTM D445	15.1	14.7	14.8	12.46


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0101769
Lab Number : 06174962
Unique Number : 11021015
Test Package : FLEET

GFL Environmental - 030 - Conway Myrtle Beach
 3010 HWY 378
 Conway, SC
 US 29527
 Contact: ARCILIO RUEZ
 aruiz@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: