



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[PMOAS2771878]

Machine Id

SD500 3004006683

Component

Diesel Engine

Fluid

DIESEL ENGINE OIL (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0028710	DC0025444	DC0017046
Sample Date		Client Info		24 Apr 2024	03 Apr 2023	10 Feb 2022
Machine Age	hrs	Client Info		199	171	135
Oil Age	hrs	Client Info		23	36	30
Filter Age	hrs	Client Info		23	36	30
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<1	5	6
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	1	5	7
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	0	2	4
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	8	8
Potassium	ppm	ASTM D5185m	>20	4	18	11
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	5.4	6.9	7.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	15.2	16.5	18.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	<1	2	3
Boron	ppm	ASTM D5185m		10	56	74
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		10	60	86
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		19	34	73
Calcium	ppm	ASTM D5185m		2246	2016	2144
Phosphorus	ppm	ASTM D5185m		912	917	1063
Zinc	ppm	ASTM D5185m		1010	1066	1172
Sulfur	ppm	ASTM D5185m		4046	3550	3283
Oxidation	Abs/.1mm	*ASTM D7414	>25	9.2	11.5	14.1
Base Number (BN)	mg KOH/g	ASTM D2896		7.5	7.6	8.3
Visc @ 100°C	cSt	ASTM D445		12.4	12.8	13.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0028710 **Received** : 10 May 2024
Lab Number : 06175171 **Tested** : 11 May 2024
Unique Number : 11021224 **Diagnosed** : 13 May 2024 - Don Baldrige
Test Package : MOB 1 (Additional Tests: TBN)

KELLY GENERATOR & EQUIPMENT INC
 1955 DALE LN
 OWINGS, MD
 US 20736
 Contact: LESLIE SNURR
 LSNURR@KGE.COM
 T: (410)257-5225
 F: (410)257-5227

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)