



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area

[W66800]

Machine Id

JOHN DEERE 624K 1DW624KZTJF685921

Component

Diesel Engine

Fluid

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: W66800)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0205933	JR0188742	JR0171403
Sample Date		Client Info		08 May 2024	27 Sep 2023	26 Jun 2023
Machine Age	hrs	Client Info		13595	12350	10972
Oil Age	hrs	Client Info		1245	1378	11724
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	16	12	12
Chromium	ppm	ASTM D5185m	>11	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	4	3	<1
Lead	ppm	ASTM D5185m	>26	0	0	0
Copper	ppm	ASTM D5185m	>26	0	0	<1
Tin	ppm	ASTM D5185m	>4	<1	5	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	5	6	6
Potassium	ppm	ASTM D5185m	>20	5	3	4
Fuel	%	ASTM D3524	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.4	0.4
Nitration	Abs/cm	*ASTM D7624	>20	7.3	8.7	9.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.0	21.9	22.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	3	4
Boron	ppm	ASTM D5185m		280	169	178
Barium	ppm	ASTM D5185m		0	1	1
Molybdenum	ppm	ASTM D5185m		104	245	212
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		467	866	797
Calcium	ppm	ASTM D5185m		1372	1406	1389
Phosphorus	ppm	ASTM D5185m		1042	906	855
Zinc	ppm	ASTM D5185m		1208	1101	1066
Sulfur	ppm	ASTM D5185m		3495	2976	3342
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.2	16.3	17.9
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	6.3	7.6	8.2
Visc @ 100°C	cSt	ASTM D445	15.4	12.7	13.5	13.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0205933 **Received** : 10 May 2024
Lab Number : 06175228 **Tested** : 13 May 2024
Unique Number : 11021281 **Diagnosed** : 13 May 2024 - Don Baldrige
Test Package : CONST (Additional Tests: FuelDilution, TBN)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269

Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

T: (704)597-0211

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

F: (704)596-6198

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)