



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
2126910
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 10W30 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0114790	PCA0106363	PCA0101128
Sample Date		Client Info		21 Apr 2024	05 Nov 2023	29 Aug 2023
Machine Age	mls	Client Info		127600	80000	60421
Oil Age	mls	Client Info		15000	20000	0
Filter Age	mls	Client Info		15000	20000	0
Oil Changed		Client Info		Not Changd	Changed	N/A
Filter Changed		Client Info		Changed	Not Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	12	13	15
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	<1	<1
Titanium	ppm	ASTM D5185m		21	<1	<1
Silver	ppm	ASTM D5185m	>3	<1	0	<1
Aluminum	ppm	ASTM D5185m	>20	3	4	11
Lead	ppm	ASTM D5185m	>40	1	4	0
Copper	ppm	ASTM D5185m	>330	48	224	365
Tin	ppm	ASTM D5185m	>15	<1	1	2
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	5	8
Potassium	ppm	ASTM D5185m	>20	6	12	29
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.2	8.0	7.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.8	19.6	19.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	<1	2
Boron	ppm	ASTM D5185m	2	16	0	3
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	50	43	62	71
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	950	805	968	1036
Calcium	ppm	ASTM D5185m	1050	1278	1161	1193
Phosphorus	ppm	ASTM D5185m	995	1015	1098	1085
Zinc	ppm	ASTM D5185m	1180	1214	1329	1316
Sulfur	ppm	ASTM D5185m	2600	3612	2857	3678
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3	15.1	14.5
Base Number (BN)	mg KOH/g	ASTM D2896		7.0	7.6	7.5
Visc @ 100°C	cSt	ASTM D445	12.00	11.2	10.8	11.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0114790 **Received** : 10 May 2024
Lab Number : 06175292 **Tested** : 13 May 2024
Unique Number : 11021345 **Diagnosed** : 13 May 2024 - Wes Davis
Test Package : FLEET

PERDUE FARMS - SALISBURY
 7036 ZION CHURCH ROAD
 SALISBURY, MD
 US 21802
 Contact: RICHARD O'NEAL
 richard.oneal@perdue.com
 T: (410)543-3628
 F: (410)341-2164

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)