



WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	NORMAL



Area
[W66955]
 Machine Id
JOHN DEERE 750K 1T0750KXHKF363027
 Component
Right Inner Final Drive
 Fluid
JOHN DEERE HY-GARD HYD/TRANS (3 GAL)

RECOMMENDATION

No corrective action is recommended at this time. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. (Customer Sample Comment: W66955)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0215430	JR0198708	JR0188668
Sample Date		Client Info		09 May 2024	15 Jan 2024	29 Sep 2023
Machine Age	hrs	Client Info		7157	6578	6002
Oil Age	hrs	Client Info		6581	576	5057
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Not Changd	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	68	10	39
Iron	ppm	ASTM D5185m	>750	78	<1	66
Chromium	ppm	ASTM D5185m	>9	<1	0	<1
Nickel	ppm	ASTM D5185m	>10	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	15	<1	1
Lead	ppm	ASTM D5185m	>15	0	<1	<1
Copper	ppm	ASTM D5185m	>40	<1	0	<1
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








Moderate concentration of visible dirt/debris present in the oil.

Silicon	ppm	ASTM D5185m	>75	39	5	8
Potassium	ppm	ASTM D5185m	>20	6	<1	0
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	▲ MODER	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	0	0	2
Boron	ppm	ASTM D5185m	6	0	<1	9
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	0	<1
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m	145	102	110	109
Calcium	ppm	ASTM D5185m	3570	3471	3443	3543
Phosphorus	ppm	ASTM D5185m	1290	1184	1055	1059
Zinc	ppm	ASTM D5185m	1640	1292	1298	1302
Sulfur	ppm	ASTM D5185m		3977	3658	3895
Visc @ 40°C	cSt	ASTM D445	57.0	52.7	58.5	52.3



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0215430 **Received** : 10 May 2024
Lab Number : 06175761 **Tested** : 14 May 2024
Unique Number : 11021814 **Diagnosed** : 14 May 2024 - Sean Felton
Test Package : CONST (Additional Tests: ICP, KV40, PQ, PrtCount, SCREEN, TAN Ma

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com
 T: (704)597-0211
 F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)