
WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[UNASSIGNED] [W66793]

F1E1YN544GATPLA00158

Right Final Drive

| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|---|------------------|--------|-------------|----------------|-------------|----------|----------|
| Resample at the next service interval to monitor. (Customer Sample Comment: W66793) | Sample Number | OOM | Client Info | Ellille / toll | JR0206029 | | |
| | Sample Date | | Client Info | | 09 May 2024 | | |
| | Machine Age | hrs | Client Info | | 456 | | |
| | Oil Age | hrs | Client Info | | 456 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | Not Changd | | |
| | Sample Status | | | | NORMAL | | |
| VEAD. | | | | | | | |
| WEAR | PQ | | ASTM D8184 | | 148 | | |
| All component wear rates are normal. | Iron | ppm | ASTM D5185m | | 217 | | |
| | Chromium | ppm | ASTM D5185m | | 2 | | |
| | Nickel | ppm | ASTM D5185m | >10 | 2 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | 0.5 | 0 | | |
| | Aluminum | ppm | ASTM D5185m | | 2 | | |
| | Lead | ppm | ASTM D5185m | | 7 | | |
| | Copper | ppm | ASTM D5185m | | 18 | | |
| | Tin | ppm | ASTM D5185m | >10 | 1 | | |
| | Vanadium | ppm | ASTM D5185m | NONE | <1 NONE | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION There is no indication of any contamination in the oil. | Silicon | ppm | ASTM D5185m | >75 | 21 | | |
| | Potassium | ppm | ASTM D5185m | >20 | 2 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 4 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | 6 | 3 | | |
| | Barium | ppm | ASTM D5185m | | 5 | | |
| | Molybdenum | ppm | ASTM D5185m | | 1 | | |
| | Manganese | ppm | ASTM D5185m | | 9 | | |
| | Magnesium | ppm | ASTM D5185m | 145 | 95 | | |
| | Calcium | ppm | ASTM D5185m | | 3415 | | |
| | Phosphorus | ppm | ASTM D5185m | | 1108 | | |
| | Zinc | ppm | ASTM D5185m | | 1187 | | |
| | Sulfur | ppm | ASTM D5185m | | 4410 | | |
| | Visc @ 40°C | cSt | ASTM D445 | F7.0 | 51.9 | | |







Laboratory Sample No. Unique Number : 11021821

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0206029 Lab Number : 06175768

Received **Tested**

Diagnosed

: 14 May 2024

: 10 May 2024

: 14 May 2024 - Sean Felton Test Package : CONST (Additional Tests: FT-IR, KV100, PQ, PrtCount, TAN Man)

CARLTON'S BACKHOE 9550 STATESVILLE ROAD CHARLOTTE, NC

US 28269 Contact: LEO

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (704)547-0211 F: