WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Machine Id


JOHN DEERE 50G 1FF050GXVMH295545

Left Final Drive

Fluid

Inot provided (--- GAL)

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0215060		
	Sample Date		Client Info		08 May 2024		
	Machine Age	hrs	Client Info		972		
	Oil Age	hrs	Client Info		972		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	238		
	Iron	ppm	ASTM D5185m		260		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		10		
	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	5		
	Lead	ppm	ASTM D5185m	>15	<1		
	Copper	ppm	ASTM D5185m	>40	3		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>75	27		
	Potassium	ppm	ASTM D5185m		25		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		- 51		
	Barium	ppm	ASTM D5185m		4		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		9		
	Magnesium	ppm	ASTM D5185m		5		
	Calcium	ppm	ASTM D5185m		90		
	Phosphorus	ppm	ASTM D5185m		555		
	Zinc	ppm	ASTM D5185m		202		
	Sulfur	ppm	ASTM D5185m		16236		
	Visc @ 40°C	cSt	ASTM D445		186		





Laboratory Sample No.

: JR0215060 Lab Number : 06175797

Unique Number : 11021850

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 10 May 2024 **Tested** : 13 May 2024

Diagnosed : 14 May 2024 - Sean Felton 9550 STATESVILLE ROAD CHARLOTTE, NC US 28269

CARLTON'S BACKHOE

Contact: LEO

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: (704)547-0211 F: