

WEAR CONTAMINATION FLUID CONDITION **ATTENTION ABNORMAL NORMAL**



Machine Id **JOHN DEERE 245P 1FF245PALNF000047**

Left Final Drive

JOHN DEERE GL-5 80W90 (GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		JR0212341		
	Sample Date		Client Info		09 May 2024		
	Machine Age	hrs	Client Info		962		
	Oil Age	hrs	Client Info		962		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
WEAR	PQ		ASTM D8184	>1250	425		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	914		
	Chromium	ppm	ASTM D5185m	>9	13		
	Nickel	ppm	ASTM D5185m	>10	2		
	Titanium	ppm	ASTM D5185m		4		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	3 0		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	2		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress.	Silicon	ppm	ASTM D5185m	>75	<u> </u>		
	Potassium	ppm	ASTM D5185m	>20	12		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		77		
	Barium	ppm	ASTM D5185m		6		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		13		
	Magnesium	ppm	ASTM D5185m		4		
	Calcium	ppm	ASTM D5185m		20		
	Phosphorus	ppm	ASTM D5185m		570		
	Zinc	ppm	ASTM D5185m		30		
	Sulfur	ppm	ASTM D5185m		18324		
	Visc @ 40°C	cSt	ASTM D445		188		





Certificate L2367

Laboratory Sample No.

Lab Number : 06175829

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0212341

Unique Number : 11021882

Received **Tested** Diagnosed Test Package : CONST (Additional Tests: PQ)

: 10 May 2024 : 13 May 2024

: 14 May 2024 - Sean Felton

JRE - ASHLAND 11047 LEADBETTER RD ASHLAND, VA US 23005

Contact: DAVID ZIEG dzieg@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (804)798-6001 F: (804)798-0292 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)