



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 700K 1T0700KXPEE270345
Component
Left Final Drive
Fluid
JOHN DEERE HY-GARD HYD/TRANS (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0211542	JR0190112	JR0168899
Sample Date		Client Info		09 May 2024	26 Oct 2023	27 Apr 2023
Machine Age	hrs	Client Info		6989	6438	5956
Oil Age	hrs	Client Info		0	6438	5956
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	49	34	49
Iron	ppm	ASTM D5185m	>750	57	18	64
Chromium	ppm	ASTM D5185m	>9	<1	<1	1
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	5	1	3
Lead	ppm	ASTM D5185m	>15	0	0	0
Copper	ppm	ASTM D5185m	>40	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	21	8	13
Potassium	ppm	ASTM D5185m	>20	2	0	2
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	0	2	2
Boron	ppm	ASTM D5185m	6	9	9	<1
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	9	6	3
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m	145	123	132	104
Calcium	ppm	ASTM D5185m	3570	3428	3212	3409
Phosphorus	ppm	ASTM D5185m	1290	1122	985	1021
Zinc	ppm	ASTM D5185m	1640	1214	1197	1248
Sulfur	ppm	ASTM D5185m		3636	3313	4245
Visc @ 40°C	cSt	ASTM D445	57.0	54.0	56.5	55.4



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0211542 **Received** : 10 May 2024
Lab Number : 06175845 **Tested** : 13 May 2024
Unique Number : 11021898 **Diagnosed** : 13 May 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)