



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**CAMILLE B BARRETT**  
Machine Id  
**[CAMILLE B BARRETT] 004 538801-4**  
Component  
**Port Reduction Gear**  
Fluid  
**CHEVRON MEROPA 220 (190 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>MW0068730</b>	MW0068676	MW0061370
Sample Date		Client Info		<b>30 Apr 2024</b>	01 Apr 2024	01 Feb 2024
Machine Age	hrs	Client Info		<b>62614</b>	61934	60479
Oil Age	hrs	Client Info		<b>62614</b>	61934	60479
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Not Changd</b>	Not Changd	Not Changd
Filter Changed		Client Info		<b>None</b>	None	None
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	<b>95</b>	120	109
Chromium	ppm	ASTM D5185m	>10	<b>0</b>	<1	<1
Nickel	ppm	ASTM D5185m	>10	<b>0</b>	2	0
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m		<b>0</b>	<1	0
Aluminum	ppm	ASTM D5185m	>25	<b>4</b>	2	2
Lead	ppm	ASTM D5185m	>100	<b>0</b>	1	0
Copper	ppm	ASTM D5185m	>50	<b>0</b>	2	0
Tin	ppm	ASTM D5185m	>10	<b>0</b>	1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**






There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	<b>1</b>	3	1
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	2	0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>8</b>	4	0
Boron	ppm	ASTM D5185m	40	<b>&lt;1</b>	3	0
Barium	ppm	ASTM D5185m		<b>1</b>	<1	0
Molybdenum	ppm	ASTM D5185m		<b>3</b>	3	1
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	2	1
Magnesium	ppm	ASTM D5185m		<b>1</b>	3	4
Calcium	ppm	ASTM D5185m		<b>23</b>	27	24
Phosphorus	ppm	ASTM D5185m	270	<b>278</b>	263	248
Zinc	ppm	ASTM D5185m		<b>11</b>	8	3
Sulfur	ppm	ASTM D5185m	8600	<b>5776</b>	5089	4747
Acid Number (AN)	mg KOH/g	ASTM D8045	0.64	<b>0.41</b>	0.40	0.33
Visc @ 40°C	cSt	ASTM D445	209	<b>317</b>	330	333



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513

**Sample No.** : MW0068730

**Lab Number** : 06176163

**Unique Number** : 11022216

**Test Package** : MAR 2

**Received** : 10 May 2024

**Tested** : 13 May 2024

**Diagnosed** : 14 May 2024 - Sean Felton

**INGRAM BARGE**

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: ANTHONY VAN CURA

anthony.vancura@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)