



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**GEORGE N**  
Machine Id  
[**GEORGE N**] 006 571099-6  
Component  
**Starboard Reduction Gear**  
Fluid  
**CHEVRON URSA SUPER PLUS 40 (10 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>MW0068103</b>	MW0067997	MW0060176
Sample Date		Client Info		<b>01 May 2024</b>	10 Apr 2024	03 Mar 2024
Machine Age	hrs	Client Info		<b>111968</b>	111500	110658
Oil Age	hrs	Client Info		<b>1295</b>	819	1299
Filter Age	hrs	Client Info		<b>1295</b>	819	1299
Oil Changed		Client Info		<b>N/A</b>	Not Changd	Not Changd
Filter Changed		Client Info		<b>N/A</b>	Not Changd	Not Changd
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	<b>3</b>	<1	5
Chromium	ppm	ASTM D5185m	>10	<b>0</b>	<1	<1
Nickel	ppm	ASTM D5185m	>10	<b>0</b>	<1	0
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	<1
Silver	ppm	ASTM D5185m		<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>25	<b>0</b>	2	3
Lead	ppm	ASTM D5185m	>100	<b>0</b>	<1	2
Copper	ppm	ASTM D5185m	>50	<b>0</b>	<1	<1
Tin	ppm	ASTM D5185m	>10	<b>&lt;1</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	<b>3</b>	4	4
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	2	1
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	0	0
Boron	ppm	ASTM D5185m		<b>378</b>	363	323
Barium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
Molybdenum	ppm	ASTM D5185m		<b>31</b>	34	32
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	0
Magnesium	ppm	ASTM D5185m		<b>9</b>	11	11
Calcium	ppm	ASTM D5185m		<b>2395</b>	2649	2405
Phosphorus	ppm	ASTM D5185m	1000	<b>716</b>	792	747
Zinc	ppm	ASTM D5185m	1090	<b>757</b>	848	791
Sulfur	ppm	ASTM D5185m		<b>3126</b>	3395	3140
Acid Number (AN)	mg KOH/g	ASTM D8045		<b>0.98</b>	1.01	0.96
Visc @ 40°C	cSt	ASTM D445	143	<b>132</b>	133	132



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : MW0068103  
**Lab Number** : 06176192  
**Unique Number** : 11022245  
**Test Package** : MAR 2

**Received** : 10 May 2024  
**Tested** : 13 May 2024  
**Diagnosed** : 13 May 2024 - Wes Davis

**INGRAM BARGE**  
 900 S 3RD ST  
 PADUCAH, KY  
 US 42003

Contact: ANTHONY VAN CURA  
 anthony.vancura@ingrambarga.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (270)415-4467  
 F: (615)695-3697