



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
DE Samples - CAT LAB
Machine Id
CATERPILLAR 980K LOADER 6775 (S/N W7K01443)
Component
Front Differential
Fluid
TULCO LUBSOIL TO-4 50 (17 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		TO10003399	TO10003113	TO10002819
Sample Date		Client Info		04 May 2024	22 Feb 2024	04 Dec 2023
Machine Age	hrs	Client Info		28486	27973	27433
Oil Age	hrs	Client Info		502	4171	3631
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		None	Not Changd	None
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ	UOM	Method	Limit/Abn	Current	History1	History2
Iron	ppm	ASTM D5185m	>500	52	47	42
Chromium	ppm	ASTM D5185m	>3	0	0	<1
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	2	3	2
Lead	ppm	ASTM D5185m	>13	0	<1	0
Copper	ppm	ASTM D5185m	>103	12	11	10
Tin	ppm	ASTM D5185m	>5	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>100	17	15	15
Potassium	ppm	ASTM D5185m	>20	0	1	0
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	5	4
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		12	13	13
Calcium	ppm	ASTM D5185m		3375	3274	3191
Phosphorus	ppm	ASTM D5185m		1013	968	942
Zinc	ppm	ASTM D5185m		1181	1183	1213
Sulfur	ppm	ASTM D5185m		5708	4765	4930
Acid Number (AN)	mg KOH/g	ASTM D8045		1.12	1.04	0.94
Visc @ 40°C	cSt	ASTM D445		212	213	213
Visc @ 100°C	cSt	ASTM D445		18.3	18.3	18.4
Viscosity Index (VI)	Scale	ASTM D2270		95	94	95



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : TO10003399 **Received** : 10 May 2024
Lab Number : 06176198 **Tested** : 13 May 2024
Unique Number : 11022251 **Diagnosed** : 13 May 2024 - Wes Davis
Test Package : MOB 2 (Additional Tests: KV100, PQ, VI)

ANCHOR STONE TULSA ROCK
 TULSA ROCK QUARRY, 66TH ST N 145TH AVENUE
 TULSA, OK
 US 74137
 Contact: MIKE SNYDER
 msnyder@anchorstoneco.com
 T: (417)850-9635
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)