



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

DANIEL P MECKLENBORG

Machine Id

[DANIEL P MECKLENBORG] 003 608409-3

Component

Starboard Main Engine

Fluid

CHEVRON DELO 710 LS (350 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0065817	MW01648178	MW0058567
Sample Date		Client Info		01 May 2024	01 Apr 2024	01 Dec 2023
Machine Age	hrs	Client Info		63679	63088	62543
Oil Age	hrs	Client Info		63679	63088	0
Filter Age	hrs	Client Info		63679	0	0
Oil Changed		Client Info		Not Changd	N/A	N/A
Filter Changed		Client Info		None	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	12	7	8
Chromium	ppm	ASTM D5185m	>8	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m	>3	0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	1	2	2
Lead	ppm	ASTM D5185m	>18	2	2	2
Copper	ppm	ASTM D5185m	>80	12	12	10
Tin	ppm	ASTM D5185m	>14	2	2	2
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	3	4	4
Potassium	ppm	ASTM D5185m	>20	<1	2	1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.7	0.8	0.7
Nitration	Abs/cm	*ASTM D7624	>20	7.9	7.5	7.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.4	15.9	15.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	1	<1	0
Boron	ppm	ASTM D5185m		44	46	45
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		43	47	45
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m		13	13	12
Calcium	ppm	ASTM D5185m		3463	3660	3408
Phosphorus	ppm	ASTM D5185m		0	10	17
Zinc	ppm	ASTM D5185m		13	3	0
Sulfur	ppm	ASTM D5185m		2763	2811	2454
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.3	8.0	7.8
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	8.39	8.78	9.59
Visc @ 100°C	cSt	ASTM D445	15.5	14.3	14.2	14.2


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0065817
Lab Number : 06176252
Unique Number : 11022305
Test Package : MAR 2
Received : 10 May 2024
Tested : 13 May 2024
Diagnosed : 13 May 2024 - Wes Davis

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003

Contact: ANTHONY VAN CURA
 anthony.vancura@ingrambarga.com
 T: (270)415-4467
 F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)