



OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**Store 1 - Cowen [RO#150387]**  
 Machine Id  
**JOHN DEERE 748L II 1DW748LBTMF711946**  
 Component  
**Front Axle**  
 Fluid  
**JOHN DEERE HY-GARD HYD/TRANS (8 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LEC0048753</b>	LEC0042205	LEC0038678
Sample Date		Client Info		<b>07 May 2024</b>	23 Oct 2023	14 Feb 2023
Machine Age	hrs	Client Info		<b>2631</b>	2064	1484
Oil Age	hrs	Client Info		<b>2060</b>	1493	913
Filter Age	hrs	Client Info		<b>1509</b>	942	362
Oil Changed		Client Info		<b>Changed</b>	Not Changd	Not Changd
Filter Changed		Client Info		<b>Changed</b>	Not Changd	Not Changd
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

PQ		ASTM D8184		<b>34</b>	31	31
Iron	ppm	ASTM D5185m	>750	<b>158</b>	139	99
Chromium	ppm	ASTM D5185m	>11	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>10	<b>1</b>	1	<1
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
Aluminum	ppm	ASTM D5185m	>21	<b>2</b>	1	0
Lead	ppm	ASTM D5185m	>49	<b>2</b>	1	1
Copper	ppm	ASTM D5185m	>101	<b>12</b>	11	8
Tin	ppm	ASTM D5185m	>10	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>31	<b>8</b>	8	6
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	0	0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	<b>7</b>	2	5
Boron	ppm	ASTM D5185m	6	<b>4</b>	0	5
Barium	ppm	ASTM D5185m	0	<b>0</b>	<1	1
Molybdenum	ppm	ASTM D5185m	0	<b>4</b>	2	4
Manganese	ppm	ASTM D5185m		<b>3</b>	3	2
Magnesium	ppm	ASTM D5185m	145	<b>71</b>	113	100
Calcium	ppm	ASTM D5185m	3570	<b>3601</b>	3363	3274
Phosphorus	ppm	ASTM D5185m	1290	<b>1125</b>	1125	929
Zinc	ppm	ASTM D5185m	1640	<b>1368</b>	1305	1157
Sulfur	ppm	ASTM D5185m		<b>4232</b>	3786	3783
Visc @ 40°C	cSt	ASTM D445	57.0	<b>52.0</b>	52.5	52.5



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : LEC0048753 **Received** : 10 May 2024  
**Lab Number** : 06176345 **Tested** : 13 May 2024  
**Unique Number** : 11022398 **Diagnosed** : 13 May 2024 - Wes Davis  
**Test Package** : CONST ( Additional Tests: PQ )

**LESLIE EQUIPMENT COMPANY**  
 105 TENNIS CENTER DR.  
 MARIETTA, OH  
 US 45750-9765  
 Contact: LEANNE KENDALL  
 KendalLeanne@lec1.com  
 T:  
 F: (740)373-5570

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)