



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

(P633847)

Machine Id

10764C

Component

Natural Gas Engine

Fluid

PETRO CANADA DURON GEO LD 15W40 (30 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0117975	GFL0101752	GFL0101801
Sample Date		Client Info		09 May 2024	23 Feb 2024	13 Feb 2024
Machine Age	hrs	Client Info		18470	17000	16561
Oil Age	hrs	Client Info		600	600	0
Filter Age	hrs	Client Info		600	600	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	9	18	12
Chromium	ppm	ASTM D5185m	>4	<1	2	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	2	1
Lead	ppm	ASTM D5185m	>30	<1	0	0
Copper	ppm	ASTM D5185m	>35	<1	2	0
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	6	9	6
Potassium	ppm	ASTM D5185m	>20	3	13	36
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	8.0	12.1	9.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.4	23.0	20.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	16	2
Boron	ppm	ASTM D5185m	50	31	9	17
Barium	ppm	ASTM D5185m	5	2	9	8
Molybdenum	ppm	ASTM D5185m	50	53	58	49
Manganese	ppm	ASTM D5185m	0	<1	<1	0
Magnesium	ppm	ASTM D5185m	560	531	599	492
Calcium	ppm	ASTM D5185m	1510	1534	1378	1388
Phosphorus	ppm	ASTM D5185m	780	802	707	625
Zinc	ppm	ASTM D5185m	870	917	918	861
Sulfur	ppm	ASTM D5185m	2040	2550	2429	2244
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.2	19.4	17.0
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	7.3	4.1	5.9
Visc @ 100°C	cSt	ASTM D445	15.1	14.6	14.7	14.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0117975
Lab Number : 06176512
Unique Number : 11022565
Test Package : FLEET

Received : 10 May 2024
Tested : 13 May 2024
Diagnosed : 13 May 2024 - Wes Davis

GFL Environmental - 030 - Conway Myrtle Beach
 3010 HWY 378
 Conway, SC
 US 29527
 Contact: ARCILIO RUEZ
 aruiz@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)