



WEAR	NORMAL
CONTAMINATION	SEVERE
FLUID CONDITION	SEVERE



Area
(YA141238)
Machine Id
2695
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (10 GAL)

RECOMMENDATION

We advise that you check the fuel injection system. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0118000	GFL0110397	GFL0088486
Sample Date		Client Info		12 May 2024	19 Mar 2024	11 Jan 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				SEVERE	SEVERE	SEVERE

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	26	51	124
Chromium	ppm	ASTM D5185m	>20	1	2	4
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	<1	2
Lead	ppm	ASTM D5185m	>40	<1	<1	12
Copper	ppm	ASTM D5185m	>330	19	4	41
Tin	ppm	ASTM D5185m	>15	2	0	2
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Silicon	ppm	ASTM D5185m	>25	3	3	6
Potassium	ppm	ASTM D5185m	>20	2	0	0
Fuel	%	ASTM D3524	>3.0	▲ 29.0	▲ 29.8	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	3.5	▲ 7.3	▲ 8
Nitration	Abs/cm	*ASTM D7624	>20	8.8	39.9	25.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3	57.9	63.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

Sodium	ppm	ASTM D5185m		0	<1	1
Boron	ppm	ASTM D5185m	0	4	4	<1
Barium	ppm	ASTM D5185m	0	2	0	0
Molybdenum	ppm	ASTM D5185m	60	43	38	32
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	1010	589	601	504
Calcium	ppm	ASTM D5185m	1070	739	703	603
Phosphorus	ppm	ASTM D5185m	1150	716	660	525
Zinc	ppm	ASTM D5185m	1270	789	779	664
Sulfur	ppm	ASTM D5185m	2060	2117	2210	1459
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.9	98.5	69.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.0	▲ 0.0	▲ 0.0
Visc @ 100°C	cSt	ASTM D445	15.4	▲ 7.8	▲ 10.2	▲ 43.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0118000 **Received** : 10 May 2024
Lab Number : 06176519 **Tested** : 15 May 2024
Unique Number : 11022572 **Diagnosed** : 15 May 2024 - Wes Davis
Test Package : FLEET (Additional Tests: PercentFuel)

GFL Environmental - 112 - New Bern
 705 Airport Road
 New Bern, NC
 US 28560
 Contact: Marquis Williams
 marquis.williams@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: