

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



Machine Id
MACK 60079
Component
Diesel Engine
Fluid

KENDALL 15W40 (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WC0867772		
	Sample Date		Client Info		17 Apr 2024		
	Machine Age	hrs	Client Info		153		
	Oil Age	hrs	Client Info		26		
	Filter Age	hrs	Client Info		26		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	\120	5		
WLAN	Chromium	ppm	ASTM D5185m		<1		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		84		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m	>330	2		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTABINATION							
CONTAMINATION	Silicon	ppm	ASTM D5185m		6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		6		
	Fuel Water		WC Method		<1.0		
			WC Method	>0.2	NEG NEG		
	Glycol Soot %	%	*ASTM D7844	- 1	0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	7.5		
	Sulfation	Abs/.1mm	*ASTM D7415		19.5		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		189		
	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m	0.4	6		
	Manganese	ppm	ASTM D5185m	077	<1		
	Magnesium	ppm	ASTM D5185m		359		
	Calcium	ppm	ASTM D5185m		1712		
	Phosphorus Zinc	ppm	ASTM D5185m ASTM D5185m		1025 1106		
	Sulfur	ppm	ASTM D5185m		3862		
	Oxidation	Abs/.1mm			3862 15.6		
	Oxidation	AUS/.IIIIII	MOTIVI D/414	>20	15.0		


Base Number (BN) mg KOH/g ASTM D2896

ASTM D445

Visc @ 100°C cSt

8.6

13.9







Certificate L2367

Laboratory Sample No.

: WC0867772 Lab Number : 06176602 Unique Number : 11022655 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 10 May 2024 : 13 May 2024 Diagnosed

: 13 May 2024 - Wes Davis

GREENEVILLE OIL & PETROLEUM INC 860 WEST ANDREW JOHNSON HWY

GREENEVILLE, TN US 37745

Contact: SHOP

shop@burkhartenterprises.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: