



Machine Id
920092-260371
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

We advise that you check the fuel injection system. The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0118769	GFL0118796	GFL0114131
Sample Date		Client Info		08 May 2024	23 Apr 2024	29 Mar 2024
Machine Age	hrs	Client Info		24135	24039	23907
Oil Age	hrs	Client Info		24761	23895	266
Filter Age	hrs	Client Info		266	266	266
Oil Changed		Client Info		Changed	Not Changd	Not Changd
Filter Changed		Client Info		Changed	Not Changd	Not Changd
Sample Status				SEVERE	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	11	10	9
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	2	2
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	3	0	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Silicon	ppm	ASTM D5185m	>25	4	6	5
Potassium	ppm	ASTM D5185m	>20	0	0	2
Fuel	%	ASTM D3524	>5	▲ 11.1	<1.0	1.9
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.5	0.3
Nitration	Abs/cm	*ASTM D7624	>20	7.2	7.2	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.5	18.7	18.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

Sodium	ppm	ASTM D5185m		4	8	4
Boron	ppm	ASTM D5185m	0	2	<1	0
Barium	ppm	ASTM D5185m	0	0	<1	0
Molybdenum	ppm	ASTM D5185m	60	50	56	56
Manganese	ppm	ASTM D5185m	0	1	0	<1
Magnesium	ppm	ASTM D5185m	1010	853	884	872
Calcium	ppm	ASTM D5185m	1070	944	981	1024
Phosphorus	ppm	ASTM D5185m	1150	902	935	1024
Zinc	ppm	ASTM D5185m	1270	1100	1155	1160
Sulfur	ppm	ASTM D5185m	2060	2955	3181	3066
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	14.5	13.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.0	7.7	8.1
Visc @ 100°C	cSt	ASTM D445	15.4	▲ 10.9	12.6	12.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : GFL0118769

Lab Number : 06176740

Unique Number : 11022793

Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

Received : 13 May 2024

Tested : 15 May 2024

Diagnosed : 15 May 2024 - Wes Davis

GFL Environmental - 837 - Harrison TS

22820 S State Route 291

Harrisonville, MO

US 64701

Contact: SARA PATRICK

spatrick@gflenv.com

T:

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)