



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
22553
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL 10W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0857089	WC0857014	WC0786394
Sample Date		Client Info		03 May 2024	21 Nov 2023	08 Aug 2023
Machine Age	hrs	Client Info		8054	7589	7075
Oil Age	hrs	Client Info		2000	1500	500
Filter Age	hrs	Client Info		2000	1500	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	12	19	14
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	3	1
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>330	3	1	2
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	6	7	4
Potassium	ppm	ASTM D5185m	>20	<1	<1	3
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	10.4	13.7	11.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	20.5	22.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	▲ MODER	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	3	1
Boron	ppm	ASTM D5185m	250	172	205	88
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	2	4	2
Manganese	ppm	ASTM D5185m		2	<1	<1
Magnesium	ppm	ASTM D5185m	450	838	286	686
Calcium	ppm	ASTM D5185m	3000	1738	3400	1902
Phosphorus	ppm	ASTM D5185m	1150	865	854	825
Zinc	ppm	ASTM D5185m	1350	1008	1123	1026
Sulfur	ppm	ASTM D5185m	4250	4365	3063	4122
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.2	18.5	23.0
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	8.6	11.2	8.1
Visc @ 100°C	cSt	ASTM D445	14.4	14.0	13.7	13.8


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Viscosity @ 100°C




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0857089
Lab Number : 06176760
Unique Number : 11022813
Test Package : CONST (Additional Tests: TBN)

SULLIVAN EASTERN INC-LIEBHERR
 2860 C SLATER RD
 MORRISVILLE, NC
 US 27560
 Contact: CHRIS CALTON

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (919)484-2136