

Machine Id JOHN DEERE 333G 1T0333GMLPF446273 Component Right Final Drive Fluid GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDATION

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

V	N	Ε	Α	R
	-	_		

Gear wear is indicated. All other metal levels are typical for a new component breaking in.

CONTAMINATION


There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0211383		
Sample Date		Client Info		10 May 2024		
Machine Age	hrs	Client Info		470		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				ABNORMAL		
DO			. 1050	07		
PQ		ASTM D8184	>1250	87		
Iron	ppm	ASTM D5185m	>750	▲ 1843		
Chromium	ppm	ASTM D5185m	>9	▲ 31 0		
Nickel	ppm	ASTM D5185m	>10	3		
Titanium	ppm	ASTM D5185m		1		
Silver	ppm	ASTM D5185m	40	0		
Aluminum	ppm	ASTM D5185m	>40	6		
Lead	ppm	ASTM D5185m	>15	0		
Copper	ppm	ASTM D5185m	>40	6		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m	NONE	<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>75	28		
Potassium	ppm	ASTM D5185m	>20	20		
Water		WC Method	>0.075	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.075	NEG		
		40TH DE105				
Sodium	ppm	ASTM D5185m	>170	11		
Boron	ppm	ASTM D5185m	400	2		
Barium	ppm	ASTM D5185m	200	78		
Molybdenum	ppm	ASTM D5185m	12	2		
Manganese	ppm	ASTM D5185m	10	18		
Magnesium	ppm	ASTM D5185m	12 150	4		
-			150	20		
Calcium	ppm	ASTM D5185m				
Calcium Phosphorus	ppm	ASTM D5185m	1650	227		
Calcium Phosphorus Zinc	ppm ppm	ASTM D5185m ASTM D5185m	1650 125	227 0		
Calcium Phosphorus	ppm	ASTM D5185m	1650	227		

Contact/Location: DAVID ZIEG - JAMASH



JRE - ASHLAND Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : JR0211383 Received 11047 LEADBETTER RD : 13 May 2024 Lab Number : 06177429 Tested ASHLAND, VA : 14 May 2024 Diagnosed : 15 May 2024 - Don Baldridge Unique Number : 11023482 US 23005 Test Package : CONST (Additional Tests: PQ) Contact: DAVID ZIEG Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. dzieg@jamesriverequipment.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (804)798-6001 F: (804)798-0292 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: DAVID ZIEG - JAMASH Page 2 of 2