**WEAR** CONTAMINATION **FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

Machine Id

## **JOHN DEERE 748L 1DW748LBKNF713779**

Front Differential

| TDH FLUID SAE 75W80 ( GAL)  |                  |        |             |           |                     |                |             |
|---|------------------|--------|-------------|-----------|---------------------|----------------|-------------|
| RECOMMENDATION  | Test             | UOM    | Method      | Limit/Abn | Current             | History1       | History2    |
| Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) TDH FLUID SAE 75W80. Please confirm. | Sample Number    |        | Client Info |           | JR0126066           |                |             |
|   | Sample Date      |        | Client Info |           | 08 May 2024         |                |             |
|   | Machine Age      | hrs    | Client Info |           | 2221                |                |             |
|   | Oil Age          | hrs    | Client Info |           | 0                   |                |             |
|   | Filter Age       | hrs    | Client Info |           | 0                   |                |             |
|   | Oil Changed      |        | Client Info |           | Not Changd          |                |             |
|   | Filter Changed   |        | Client Info |           | N/A                 |                |             |
|   | Sample Status    |        |             |           | NORMAL              |                |             |
| WEAR  | PQ               |        | ASTM D8184  |           | 57                  |                |             |
| All component wear rates are normal.  | Iron             | ppm    | ASTM D5185m | >500      | 182                 |                |             |
|   | Chromium         | ppm    | ASTM D5185m | >10       | <1                  |                |             |
|   | Nickel           | ppm    | ASTM D5185m | >10       | 0                   |                |             |
|   | Titanium         | ppm    | ASTM D5185m |           | <1                  |                |             |
|   | Silver           | ppm    | ASTM D5185m |           | 0                   |                |             |
|   | Aluminum         | ppm    | ASTM D5185m |           | 1                   |                |             |
|   | Lead             | ppm    | ASTM D5185m |           | 2                   |                |             |
|   | Copper           | ppm    | ASTM D5185m |           | 25                  |                |             |
|   | Tin              | ppm    | ASTM D5185m | >10       | 2                   |                |             |
|   | Vanadium         | ppm    | ASTM D5185m | NONE      | 0                   |                |             |
|   | White Metal      | scalar | *Visual     | NONE      | NONE                |                |             |
|   | Yellow Metal     | scalar | *Visual     | NONE      | NONE                |                |             |
| CONTAMINATION   | Silicon          | ppm    | ASTM D5185m | >75       | 7                   |                |             |
| There is no indication of any contamination in the oil.   | Potassium        | ppm    | ASTM D5185m | >20       | 0                   |                |             |
|   | Water            |        | WC Method   | >.2       | NEG                 |                |             |
|   | Silt             | scalar | *Visual     | NONE      | NONE                |                |             |
|   | Debris           | scalar | *Visual     | NONE      | NONE                |                |             |
|   | Sand/Dirt        | scalar | *Visual     | NONE      | NONE                |                |             |
|   | Appearance       | scalar | *Visual     | NORML     | NORML               |                |             |
|   | Odor             | scalar | *Visual     | NORML     | NORML               |                |             |
| <u></u>   | Emulsified Water | scalar | *Visual     | >.2       | NEG                 |                |             |
| FLUID CONDITION   | Sodium           | ppm    | ASTM D5185m |           | 7                   |                |             |
| The condition of the oil is acceptable for the time in service.   | Boron            | ppm    | ASTM D5185m | 10        | 1                   |                |             |
|   | Barium           | ppm    | ASTM D5185m |           | 1                   |                |             |
|   | Molybdenum       | ppm    | ASTM D5185m | 10        | 0                   |                |             |
|   | Manganese        | ppm    | ASTM D5185m |           | 8                   |                |             |
|   | Magnesium        | ppm    | ASTM D5185m |           | 98                  |                |             |
|   | Calcium          | ppm    | ASTM D5185m | 3500      | 3354                |                |             |
|   | Phosphorus       | ppm    | ASTM D5185m |           | 1045                |                |             |
|   | Zinc             | ppm    | ASTM D5185m |           | 1224                |                |             |
|   | Sulfur           | ppm    | ASTM D5185m |           | 4385                |                |             |
| Report Id: JAMSALJR (WLISCAR) 06177443 (Generated: 05/14/2024 13:15:08) Rev: 1  | Visc @ 40°C      | cSt    | ASTM D445   | 48        | 50.7<br>Submitted F | <br>N: BRETT I | <br>ΔWRENCE |





Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

: JR0126066 Lab Number : 06177443

Unique Number : 11023496

Diagnosed Test Package : MOBCE ( Additional Tests: PQ ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

: 14 May 2024 : 14 May 2024 - Wes Davis

: 13 May 2024

JRE - SALEM 3902 W. MAIN STREET SALEM, VA

US 24153 Contact: BRETT LAWRENCE

brett.lawrence@jamesriverequipment.com T:

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received

**Tested** 

F: (540)380-5547