



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[05W46607]
 Machine Id
JOHN DEERE 850K 1T0850KXKLF369647
 Component
Left Inner Final Drive
 Fluid
JOHN DEERE HY-GARD HYD/TRANS (3 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0214379	JR0192138	JR0169093
Sample Date		Client Info		10 May 2024	20 Nov 2023	12 Apr 2023
Machine Age	hrs	Client Info		5467	4980	4443
Oil Age	hrs	Client Info		487	4503	477
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		N/A	None	None
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	39	18	23
Iron	ppm	ASTM D5185m	>750	45	26	20
Chromium	ppm	ASTM D5185m	>9	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>40	<1	2	4
Lead	ppm	ASTM D5185m	>15	0	0	0
Copper	ppm	ASTM D5185m	>40	3	<1	<1
Tin	ppm	ASTM D5185m	>10	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	8	10	13
Potassium	ppm	ASTM D5185m	>20	0	2	0
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	2	0	<1
Boron	ppm	ASTM D5185m	6	8	9	9
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	5	9	8
Manganese	ppm	ASTM D5185m		2	<1	<1
Magnesium	ppm	ASTM D5185m	145	127	129	125
Calcium	ppm	ASTM D5185m	3570	3510	3507	3434
Phosphorus	ppm	ASTM D5185m	1290	1039	1066	993
Zinc	ppm	ASTM D5185m	1640	1272	1283	1223
Sulfur	ppm	ASTM D5185m		4102	3807	4079
Visc @ 40°C	cSt	ASTM D445	57.0	52.5	51.4	51.8



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0214379 **Received** : 13 May 2024
Lab Number : 06177478 **Tested** : 14 May 2024
Unique Number : 11023531 **Diagnosed** : 14 May 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

CWS-STRITTMATTER
 9102 OWENS DR
 MANASSAS PARK, VA
 US 20111
 Contact: EDDIE GARRETSON
 egarretson@strittmattercompanies.com
 T: (703)335-2255
 F: (703)335-8095

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)