

RECOMMENDATION

Current

History1

History2

Limit/Abn

Machine Id VOLVO A40G 752211 Component

Transmission (Auto)

VOLVO AUTOMATIC TRANSMISSION FLUID AT102 (--- GAL)

Test

UOM

Method

		00			••••••	
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP449625	
	Sample Date		Client Info		07 May 2024	
	Machine Age	hrs	Client Info		761	
	Oil Age	hrs	Client Info		0	
	Filter Age	hrs	Client Info		0	
	Oil Changed		Client Info		Not Changd	
	Filter Changed		Client Info		Not Changd	
	Sample Status				NORMAL	
				4.00	<u></u>	
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m		31	
	Chromium	ppm	ASTM D5185m		0	
	Nickel	ppm	ASTM D5185m	>5	3	
	Titanium	ppm	ASTM D5185m	_	0	
	Silver	ppm	ASTM D5185m		0	
	Aluminum	ppm	ASTM D5185m		19	
	Lead	ppm	ASTM D5185m		<1	
	Copper	ppm	ASTM D5185m		33	
	Tin	ppm	ASTM D5185m	>10	5	
	Vanadium	ppm	ASTM D5185m		0	
	White Metal	scalar	*Visual	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	14	
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m	>20	1	
	Water		WC Method	>0.1	NEG	
	Silt	scalar	*Visual	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	
FLUID CONDITION					<u> </u>	
	Sodium	ppm	ASTM D5185m	107	6	
The condition of the fluid is acceptable for the time in service.	Boron Barium	ppm	ASTM D5185m ASTM D5185m		80	
	Molybdenum	ppm	ASTM D5185m		<1	
	-	ppm			0	
	Manganese	ppm	ASTM D5185m		5	
	Magnesium	ppm	ASTM D5185m		0	
	Calcium	ppm	ASTM D5185m		72	
	Phosphorus	ppm	ASTM D5185m		187	
	Zinc	ppm	ASTM D5185m		8	
	Sulfur	ppm	ASTM D5185m	1336	2102	


Contact/Location: TODD LARK - VOLVO0090


29.5


ASTM D445 35.3

Visc @ 40°C

cSt







Contact/Location: TODD LARK - VOLVO0090 Page 2 of 2