



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
MARTHA INGRAM
Machine Id
[**MARTHA INGRAM**] 001 589419-1
Component
Port Main Engine
Fluid
CHEVRON DELO 710 LS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0061466	MW0063274	MW0053587
Sample Date		Client Info		01 May 2024	01 Mar 2024	01 Aug 2023
Machine Age	hrs	Client Info		16704	19460	10338
Oil Age	hrs	Client Info		16704	19460	10338
Filter Age	hrs	Client Info		320	19460	469
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	None	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	9	9	17
Chromium	ppm	ASTM D5185m	>8	1	<1	2
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	1	1	4
Lead	ppm	ASTM D5185m	>18	2	4	5
Copper	ppm	ASTM D5185m	>80	9	13	13
Tin	ppm	ASTM D5185m	>14	3	3	4
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	3	3	7
Potassium	ppm	ASTM D5185m	>20	<1	0	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1	0.2	1.5
Nitration	Abs/cm	*ASTM D7624	>20	8.8	9.6	9.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.5	17.0	18.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	9	<1	16
Boron	ppm	ASTM D5185m		40	38	36
Barium	ppm	ASTM D5185m		1	0	0
Molybdenum	ppm	ASTM D5185m		45	43	48
Manganese	ppm	ASTM D5185m		2	1	<1
Magnesium	ppm	ASTM D5185m		12	12	10
Calcium	ppm	ASTM D5185m		3351	3379	3717
Phosphorus	ppm	ASTM D5185m		5	10	7
Zinc	ppm	ASTM D5185m		0	1	6
Sulfur	ppm	ASTM D5185m		2567	2528	2575
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.6	10.4	8.2
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	9.20	9.62	9.54
Visc @ 100°C	cSt	ASTM D445	15.5	15.2	15.2	15.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0061466
Lab Number : 06177895
Unique Number : 11029221
Test Package : MAR 2
Received : 13 May 2024
Tested : 14 May 2024
Diagnosed : 14 May 2024 - Wes Davis

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003
 Contact: ANTHONY VAN CURA
 anthony.vancura@ingrambarga.com
 T: (270)415-4467
 F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)