

Area
KEMP QUARRIES / BCS - GRAVETTE [69378]

Machine Id
OHT119
Component
Rear Right Final Drive

Fluid
PETRO CANADA TRAXON 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: Pm4)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0108525	PCA0084766	PCA0085713
Sample Date		Client Info		22 Apr 2024	30 Nov 2023	11 May 2023
Machine Age	hrs	Client Info		26752	26752	26286
Oil Age	hrs	Client Info		25218	25684	26286
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	77	86	60
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	3	0
Lead	ppm	ASTM D5185m	>25	<1	2	<1
Copper	ppm	ASTM D5185m	>50	6	9	5
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	12	17	18
Potassium	ppm	ASTM D5185m	>20	0	2	0
Water		WC Method	>0.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<1	0	1
Boron	ppm	ASTM D5185m	243	121	66	2
Barium	ppm	ASTM D5185m	1	1	8	11
Molybdenum	ppm	ASTM D5185m		0	2	1
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m	2	43	45	55
Calcium	ppm	ASTM D5185m	6	1310	2030	2430
Phosphorus	ppm	ASTM D5185m	987	948	1025	868
Zinc	ppm	ASTM D5185m	1	621	929	1013
Sulfur	ppm	ASTM D5185m	21530	11202	9308	4882
Visc @ 40°C	cSt	ASTM D445	141.0	130	139	155



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0108525
Lab Number : 06177937
Unique Number : 11029263
Test Package : MOB 1

Received : 13 May 2024
Tested : 14 May 2024
Diagnosed : 15 May 2024 - Sean Felton

Kemp Quarries - Benton County Stone - Gravette
 15100 N Hwy 59
 Sulphur Springs, AR
 US 72768

Contact: gravette@bentoncountystone.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: