



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1241
Component
Diesel Engine
Fluid
SHELL ROTELLA T 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0626073	WC0626072	WC0626074
Sample Date		Client Info		04 May 2024	22 Nov 2023	28 Apr 2023
Machine Age	mls	Client Info		136650	124984	101408
Oil Age	mls	Client Info		11666	11305	11418
Filter Age	mls	Client Info		11666	11305	11418
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	28	24	24
Chromium	ppm	ASTM D5185m	>20	3	2	3
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	13	8	16
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	1	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	6	6
Potassium	ppm	ASTM D5185m	>20	9	5	10
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	8.1	7.8	6.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	20.6	18.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	0
Boron	ppm	ASTM D5185m	316	90	63	82
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	1.2	64	61	66
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	24	371	395	427
Calcium	ppm	ASTM D5185m	2292	1665	1755	1876
Phosphorus	ppm	ASTM D5185m	1064	1030	1010	1047
Zinc	ppm	ASTM D5185m	1160	1202	1225	1263
Sulfur	ppm	ASTM D5185m	4996	3409	3121	3771
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.7	18.5	15.5
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	7.7	7.5	7.2
Visc @ 100°C	cSt	ASTM D445	15.7	12.5	12.5	12.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0626073
Lab Number : 06178580
Unique Number : 11029906
Test Package : MOB1+
Received : 14 May 2024
Tested : 15 May 2024
Diagnosed : 15 May 2024 - Wes Davis

CARCO TRANSPORTATION
 900 WEST JOHNSON AVE
 JONESBORO, AR
 US 72401
 Contact: DAVID GLIDEWELL
 dglidewell@carcotrans.com
 T: (870)935-1424
 F: (870)935-3433

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)