WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

JOHN DEERE 948L 1DW948LBPPF717034

Hydraulic System

JOHN DEERE HYDRAU (--- QTS)

JOHN DEERE HYDRAU (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		WE0006855	WE0005780	
Resample at the next service interval to monitor.	Sample Date		Client Info		08 May 2024	07 Dec 2023	
	Machine Age	hrs	Client Info		1066	612	
	Oil Age	hrs	Client Info		0	612	
	Filter Age	hrs	Client Info		0	612	
	Oil Changed		Client Info		N/A	Not Changd	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	ATTENTION	
VEAR	PQ		ASTM D8184		16	14	
	Iron	ppm	ASTM D5185m	>20	0	<1	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	1	
	Nickel	ppm	ASTM D5185m		0	<1	
	Titanium	ppm	ASTM D5185m	>10	0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>10	0	1	
	Lead	ppm	ASTM D5185m		0	1	
	Copper		ASTM D5185m		0	1	
	Tin	ppm	ASTM D5185m		0 <1	0	
	Vanadium	ppm	ASTM D5185m	>10	0	<1	
	White Metal	ppm	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.	0.00		AOTM DEADE		• • • • • • • • • • • • • • • • • • • •		
	Silicon	ppm	ASTM D5185m		0	3	
	Potassium	ppm	ASTM D5185m		0	8	
	Water		WC Method		NEG	NEG	
	railicles >4µIII		ASTM D7647		753	5195	
	Particles >6µm		ASTM D7647		142	394	
	Particles >14µm		ASTM D7647		13	34	
	Particles >21µm		ASTM D7647		4	12	
	Particles >38μm		ASTM D7647		1	2	
	Particles >71µm		ASTM D7647		1	0	
	Oil Cleanliness		ISO 4406 (c)	>19/17/14	17/14/11	0 20/16/12	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
LUID CONDITION	Sodium	ppm	ASTM D5185m		0	<1	
7 AND 12 11 7 11 7 11 7 11 7 11 7 11 7 11 7	Boron	ppm	ASTM D5185m		0	0	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	s Barium	ppm	ASTM D5185m		1	0	
	Molybdenum	ppm	ASTM D5185m		0	<1	
	Manganese	ppm	ASTM D5185m		0	0	
	Magnesium	ppm	ASTM D5185m		2	2	
	Calcium	ppm	ASTM D5185m	87	94	143	
	Phosphorus	ppm	ASTM D5185m		711	774	
	Zinc	ppm	ASTM D5185m	900	862	1030	
	Sulfur	ppm	ASTM D5185m		1827	2069	
	Acid Number (AN) Visc @ 40°C	mg KOH/g cSt	ASTM D8045 ASTM D445		0.70 64.0	0.62 58.2	





Certificate L2367

Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 06178588 Unique Number: 11029914

: WE0006855

Received : 14 May 2024 **Tested**

: 15 May 2024 : 15 May 2024 - Wes Davis Diagnosed Test Package : CONST (Additional Tests: PQ)

WARRIOR TRACTOR AND EQUIPMENT - NORTHPORT P.O. BOX 412 NORTHPORT, AL

US 35476 Contact: CRAIG ANDOE

serve01@warriortractor.com T: (205)339-0300

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: