



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
PAUL F BROTZGE
Component
Port Reduction Gear
Fluid
CHEVRON MEROPA 220 (220 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0069290	MW0053170	MW0066417
Sample Date		Client Info		01 May 2024	01 Apr 2024	02 Mar 2024
Machine Age	hrs	Client Info		63335	62622	61902
Oil Age	hrs	Client Info		63335	62622	61902
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		None	None	None
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	61	94	98
Chromium	ppm	ASTM D5185m	>10	1	<1	<1
Nickel	ppm	ASTM D5185m	>10	1	<1	<1
Titanium	ppm	ASTM D5185m		1	<1	<1
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>25	4	3	4
Lead	ppm	ASTM D5185m	>100	2	1	<1
Copper	ppm	ASTM D5185m	>50	11	11	12
Tin	ppm	ASTM D5185m	>10	1	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	6	9	6
Potassium	ppm	ASTM D5185m	>20	4	2	1
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		18	27	28
Boron	ppm	ASTM D5185m	40	<1	<1	1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	0	3
Manganese	ppm	ASTM D5185m		1	1	1
Magnesium	ppm	ASTM D5185m		1	0	3
Calcium	ppm	ASTM D5185m		20	19	27
Phosphorus	ppm	ASTM D5185m	270	129	207	238
Zinc	ppm	ASTM D5185m		2	0	0
Sulfur	ppm	ASTM D5185m	8600	3351	4973	5765
Acid Number (AN)	mg KOH/g	ASTM D8045	0.64	0.81	0.82	0.86
Visc @ 40°C	cSt	ASTM D445	209	227	232	231



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0069290
Lab Number : 06186360
Unique Number : 11043112
Test Package : MAR 2

Received : 21 May 2024
Tested : 22 May 2024
Diagnosed : 22 May 2024 - Wes Davis

AMERICAN COMMERCIAL LINES
 PO BOX 610, 1701 E. MARKET STREET
 JEFFERSONVILLE, IN
 US 47130
 Contact: RONALD SCHNEIDER
 ronald.schneider@bargeacbl.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (812)288-1644