



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[ILA PROPERTIES]

Machine Id

JOHN DEERE 350G 1FF350GXEMF815195

Component

Left Final Drive

Fluid

JOHN DEERE GL-5 80W90 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0195497	JR0174662	JR0153554
Sample Date		Client Info		16 May 2024	06 Jun 2023	28 Nov 2022
Machine Age	hrs	Client Info		1997	1435	1020
Oil Age	hrs	Client Info		0	1435	1020
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	347	206	282
Iron	ppm	ASTM D5185m	>750	492	416	366
Chromium	ppm	ASTM D5185m	>9	6	6	5
Nickel	ppm	ASTM D5185m	>10	0	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	4	1	2
Lead	ppm	ASTM D5185m	>15	0	0	0
Copper	ppm	ASTM D5185m	>40	<1	1	1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	LIGHT	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	31	25	20
Potassium	ppm	ASTM D5185m	>20	0	1	0
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	LIGHT	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	VLITE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	1	<1	<1
Boron	ppm	ASTM D5185m		71	74	72
Barium	ppm	ASTM D5185m		4	3	0
Molybdenum	ppm	ASTM D5185m		8	<1	<1
Manganese	ppm	ASTM D5185m		8	8	6
Magnesium	ppm	ASTM D5185m		28	2	1
Calcium	ppm	ASTM D5185m		81	29	25
Phosphorus	ppm	ASTM D5185m		520	540	469
Zinc	ppm	ASTM D5185m		50	26	14
Sulfur	ppm	ASTM D5185m		16960	18620	16922
Visc @ 40°C	cSt	ASTM D445		184	184	184



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0195497 **Received** : 21 May 2024
Lab Number : 06186519 **Tested** : 22 May 2024
Unique Number : 11043271 **Diagnosed** : 22 May 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

JRE - STEPHENSON
 245 YARDMASTER COURT
 STEPHENSON, VA
 US 22656-1761
 Contact: PHIL DAUGHERTY
 pdaugherty@jamesriverequipment.com
 T: x:
 F: (540)693-2588

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)