



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>ATTENTION</b>
FLUID CONDITION	<b>NORMAL</b>

Area

**[05W46860]**

Machine Id

**JOHN DEERE 324G 1T0324GMHPJ433658**

Component

**Hydraulic System**

Fluid

**JOHN DEERE HYDRAU (7 GAL)**

### RECOMMENDATION

No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>JR0214342</b>	JR0199444	---
Sample Date		Client Info		<b>17 May 2024</b>	05 Jan 2024	---
Machine Age	hrs	Client Info		<b>1021</b>	510	---
Oil Age	hrs	Client Info		<b>1021</b>	510	---
Filter Age	hrs	Client Info		<b>511</b>	510	---
Oil Changed		Client Info		<b>Changed</b>	Not Changd	---
Filter Changed		Client Info		<b>Changed</b>	Changed	---
Sample Status				<b>ATTENTION</b>	SEVERE	---

### WEAR

All component wear rates are normal.

Test	UOM	Method	Limit/Abn	Current	History1	History2
PQ		ASTM D8184		<b>23</b>	20	---
Iron	ppm	ASTM D5185m	>20	<b>22</b>	13	---
Chromium	ppm	ASTM D5185m	>10	<b>3</b>	<1	---
Nickel	ppm	ASTM D5185m	>10	<b>&lt;1</b>	0	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Silver	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Aluminum	ppm	ASTM D5185m	>10	<b>3</b>	<1	---
Lead	ppm	ASTM D5185m	>10	<b>2</b>	0	---
Copper	ppm	ASTM D5185m	>75	<b>13</b>	13	---
Tin	ppm	ASTM D5185m	>10	<b>&lt;1</b>	0	---
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---

### CONTAMINATION










There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.

Silicon	ppm	ASTM D5185m	>20	<b>3</b>	2	---
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	1	---
Water		WC Method	>0.1	<b>NEG</b>	NEG	---
Particles >4µm		ASTM D7647	>5000	<b>5799</b>	▲ 67909	---
Particles >6µm		ASTM D7647	>1300	<b>199</b>	▲ 4995	---
Particles >14µm		ASTM D7647	>160	<b>8</b>	30	---
Particles >21µm		ASTM D7647	>40	<b>3</b>	5	---
Particles >38µm		ASTM D7647	>10	<b>0</b>	0	---
Particles >71µm		ASTM D7647	>3	<b>0</b>	0	---
Oil Cleanliness		ISO 4406 (c)	>19/17/14	<b>20/15/10</b>	▲ 23/19/12	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	---

### FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	1	---
Boron	ppm	ASTM D5185m		<b>0</b>	0	---
Barium	ppm	ASTM D5185m		<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Magnesium	ppm	ASTM D5185m		<b>3</b>	1	---
Calcium	ppm	ASTM D5185m	87	<b>192</b>	159	---
Phosphorus	ppm	ASTM D5185m	727	<b>574</b>	665	---
Zinc	ppm	ASTM D5185m	900	<b>771</b>	774	---
Sulfur	ppm	ASTM D5185m	1500	<b>1870</b>	1674	---
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	<b>0.65</b>	0.82	---
Visc @ 40°C	cSt	ASTM D445	65	<b>48.5</b>	50.3	---



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0214342 **Received** : 21 May 2024  
**Lab Number** : 06186641 **Tested** : 23 May 2024  
**Unique Number** : 11043393 **Diagnosed** : 23 May 2024 - Don Baldrige  
**Test Package** : CONST ( Additional Tests: PQ )

**JRE - MANASSAS PARK**  
 9107 OWENS DRIVE  
 MANASSAS PARK, VA  
 US 20111  
 Contact: DON VEST  
 dvest@jamesriverequipment.com  
 T: (703)631-8500  
 F: (703)631-4715

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)