

## Machine Id SM312/013 FEED WORKS OPTIMIL (S/N 0238-32110-00180-04801) Component Hydraulic System Fluid AW HYDRAULIC OIL ISO 68 (--- GAL)

## RECOMMENDATION

Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. We advise that you check all areas where contaminants can enter the system. We advise that you perform a filter service, and use offline filtration to improve the cleanliness of the system fluid. The air breather requires service. If unrated, we recommend that you replace with a suitable micron rated and/or desiccant air breather. If rated, we recommend that you service/replace the breather. Resample in 30-45 days to monitor this situation. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

## WEAR

All component wear rates are normal.

## CONTAMINATION

There is a high amount of particulates (2 to 100 microns in size) present in the oil. The system cleanliness code is much higher than the acceptable limit for the target ISO 4406 cleanliness code.

-----

		$\mathbf{c}$	NDI	N
FLU	U		וטא	

The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.

Test		Method	l imit/Abn	Current	History1	History?
Sample Number	00101	Client Info	LITTIUAUT	EC006220	FC006179	FC0000568
Sample Date		Client Info		17 May 2024	27 Eeb 2024	15 Aug 2023
Machine Age	hre	Client Info		17 May 2024	0	0
	hre	Client Info		0	0	0
Filter Age	hre	Client Info		0	0	0
Oil Changed	1113	Client Info		N/Δ	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				SEVERE	ABNORMAL	ABNORMAL
Iron	ppm	ASTM D5185m	>20	0	0	<1
Chromium	ppm	ASTM D5185m	>20	0	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	0	0	<1
Lead	ppm	ASTM D5185m	>20	0	0	0
Copper	ppm	ASTM D5185m	>20	4	0	4
Tin	ppm	ASTM D5185m	>20	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Silicon	nnm	ASTM D5185m	<u>\15</u>	3	~1	2
Potassium	ppm	ASTM D5185m	>20	د د1	0	0
Water	PP	WC Method	>0.05	NEG	NEG	NEG
Particles >4um		ASTM D7647	>320	<b>3167</b>	1968	470
Particles >6um		ASTM D7647	>80	▲ 803	<b>4</b> 14	<b>1</b> 69
Particles >14µm		ASTM D7647	>10	▲ 38	<b>4</b> 34	<u> </u>
Particles >21µm		ASTM D7647	>3	<b>4</b> 9	<b>1</b> 0	<u> </u>
Particles >38µm		ASTM D7647	>3	0	1	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>15/13/10	<b>1</b> 9/17/12	▲ 18/16/12	▲ 16/15/12
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Sodium	nom	ASTM D5185m		1	0	0
Boron	ppm	ASTM D5185m	5	0	0	0
Barium	ppm	ASTM D5185m	5	0	1	0
Molybdenum	ppm	ASTM D5185m	5	<1	0	<1
Manganese	mag	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	25	3	5	2
Calcium	ppm	ASTM D5185m	200	63	64	65
Phosphorus	ppm	ASTM D5185m	300	329	321	321
Zinc	ppm	ASTM D5185m	370	378	379	371
Sulfur	ppm	ASTM D5185m	2500	3639	2917	3546
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.31	0.29	0.27
Visc @ 40°C	cSt	ASTM D445	68	63.4	63.9	63.1



To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: Duane Smith - FLUMAR Page 2 of 2

T: (770)509-5833

F: (770)509-5832