**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 

**AIRLUBE** 

## ELGI MUFS04698 - VRC METAL SYSTEM Component Compressor

······							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		UCH06187829		
	Sample Date		Client Info		15 May 2024		
	Machine Age	hrs	Client Info		6000		
	Oil Age	hrs	Client Info		6000		
	Filter Age	hrs	Client Info		6000		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>50	<1		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>25	1		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>50	<1		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTANUNATION							
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		8		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		4		
	Phosphorus	ppm	ASTM D5185m		4		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		0		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.34		
	Visc @ 40°C	cSt	ASTM D445		46.3		







Certificate L2367

Laboratory Sample No.

: UCH06187829 Lab Number : 06187829 Unique Number : 11044581 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

Diagnosed

: 22 May 2024 : 23 May 2024

: 23 May 2024 - Wes Davis

0.10 0.08 0.06 0.04

0.02

0.00

8131 VIRGINIA PINE CT RICHMOND, VA US 23237 Contact: JOE MYRICK

**TATE ENGINEERING** 

JOE.MYRICK@TATE.COM T: (804)339-0007

To discuss this sample report, contact Customer Service at 1-800-237-1369.

39

38

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (804)743-0415