WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL


OIL ANALYSIS REPORT

Machine Id

LEB REC 1

Gearbox

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Sample Number	OCIVI	Client Info	LIIIIII/ADII	TR06187849	TR05936282	
	Sample Date		Client Info		15 May 2024	01 Jun 2023	
	Machine Age	yrs	Client Info		0	0	
	Oil Age	yrs	Client Info		2	1	
	Filter Age		Client Info		0	0	
	Oil Changed	yrs	Client Info		N/A	N/A	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status		Client inio		NORMAL	NORMAL	
	Sample Status					NONWAL	
VEAR	Iron	ppm	ASTM D5185m	>200	5	8	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1	0	
	Nickel	ppm	ASTM D5185m		<1	0	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		<1	0	
	Aluminum	ppm	ASTM D5185m	>25	2	0	
	Lead	ppm	ASTM D5185m	>50	1	0	
	Copper	ppm	ASTM D5185m	>200	<1	0	
	Tin	ppm	ASTM D5185m	>10	<1	0	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	O'''		AOTA DELOE				
CONTAMINATION	Silicon	ppm	ASTM D5185m		10	11	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		2	3	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris Sand/Dist	scalar	*Visual	NONE	NONE NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE		NONE NORML	
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML NEG	NORML	
<u></u>	Emulsified Water	scalar	*Visual	>0.2		NEG	
LUID CONDITION	Sodium	ppm	ASTM D5185m		4	<1	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		242	282	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		0	0	
	Manganese	ppm	ASTM D5185m		0	<1	
	Magnesium	ppm	ASTM D5185m		2	3	
	Calcium	ppm	ASTM D5185m		32	30	
	Phosphorus	ppm	ASTM D5185m		871	1049	
	Zinc	ppm	ASTM D5185m		21	7	
	Sulfur	ppm	ASTM D5185m		18080	24337	
	Acid Number (AN)	mg KOH/g	ASTM D8045		2.03	1.84	
	Visc @ 40°C	cSt	ASTM D445	186	160	163	
	Visc @ 40°C Visc @ 100°C	cSt cSt	ASTM D445 ASTM D445		160 18.3	163 18.6	





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

: TR06187849 Lab Number : 06187849 Unique Number : 11044601

Tested Diagnosed Test Package : MOB 2 (Additional Tests: KV100, VI)

Received : 22 May 2024 : 23 May 2024

: 23 May 2024 - Wes Davis

CHRIST BROTHERS PRODUCTS 820 S FRITZ LEBANON, IL

US 62254 Contact: BRUCE COWELL

Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-827-0711.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: