**OIL ANALYSIS REPORT** 

**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 


Machine Id

## LEB REC COL

Gearbox

TRC MOLY III TRA-TEC GEAR OIL 80W90 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Sample Number		Client Info		TR06187879	TR05936291	
	Sample Date		Client Info		15 May 2024	01 Jun 2023	
	Machine Age	yrs	Client Info		0	0	
	Oil Age	yrs	Client Info		2	1	
	Filter Age	yrs	Client Info		0	0	
	Oil Changed		Client Info		N/A	N/A	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
VEAR	Iron	ppm	ASTM D5185m	>200	9	10	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1	0	
	Nickel	ppm	ASTM D5185m		<1	0	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		<1	0	
	Aluminum	ppm	ASTM D5185m	>25	1	0	
	Lead	ppm	ASTM D5185m		<1	0	
	Copper	ppm	ASTM D5185m	>200	2	0	
	Tin	ppm	ASTM D5185m		<1	0	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon		ACTM DE10Em	. 50	44	A	
CONTAMINATION		ppm	ASTM D5185m		11	4	
There is no indication of any contamination in the oil.	Potassium Water	ppm	ASTM D5185m WC Method		2 NEG	0 NEG	
	Silt	cooler	*Visual	NONE	NONE	NONE	
	Debris	scalar scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
THIR CONDITION	0 "		40TM D5405				
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2	3	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		300	265 0	
	Barium Molybdenum	ppm	ASTM D5185m ASTM D5185m		0 <1	0	
	Manganese	ppm	ASTM D5185m		0	<1	
	Magnesium	ppm	ASTM D5185m		<1	2	
	Calcium	ppm	ASTM D5185m		26	14	
	Phosphorus	ppm	ASTM D5185m		1034	860	
	Zinc	ppm	ASTM D5185m		18	3	
	Sulfur	ppm	ASTM D5185m		21437	20434	
	Acid Number (AN)	mg KOH/g	ASTM D3103111		2.01	1.47	
	Visc @ 40°C	cSt	ASTM D0045	186	151	157	
	•				16.8	17.6	
	Visc @ 100°C	cSt	ASTM D445	19.3	וף.א	/h	







Laboratory Sample No.

Lab Number : 06187879

: TR06187879 Unique Number : 11044631

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** Diagnosed

: 23 May 2024

: 23 May 2024 - Wes Davis

: 22 May 2024

820 S FRITZ LEBANON, IL US 62254

Contact: BRUCE COWELL

**CHRIST BROTHERS PRODUCTS** 

Test Package : MOB 2 (Additional Tests: KV100, VI) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-827-0711.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: