



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 410E-II 1DW410ELKNF713302
Component
Front Differential
Fluid
JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0213296	JR0194444	JR0187204
Sample Date		Client Info		21 May 2024	04 Jan 2024	20 Sep 2023
Machine Age	hrs	Client Info		2236	1537	1099
Oil Age	hrs	Client Info		0	0	1099
Filter Age	hrs	Client Info		0	0	682
Oil Changed		Client Info		N/A	N/A	Not Changd
Filter Changed		Client Info		N/A	N/A	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		24	12	30
Iron	ppm	ASTM D5185m	>500	54	0	35
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	<1	1
Lead	ppm	ASTM D5185m	>25	21	0	17
Copper	ppm	ASTM D5185m	>100	10	0	6
Tin	ppm	ASTM D5185m	>10	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	5	5	7
Potassium	ppm	ASTM D5185m	>20	0	0	0
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		6	0	6
Boron	ppm	ASTM D5185m	6	0	47	2
Barium	ppm	ASTM D5185m	0	6	0	0
Molybdenum	ppm	ASTM D5185m	0	1	40	4
Manganese	ppm	ASTM D5185m		2	<1	1
Magnesium	ppm	ASTM D5185m	145	98	216	102
Calcium	ppm	ASTM D5185m	3570	3377	2952	3379
Phosphorus	ppm	ASTM D5185m	1290	876	1014	997
Zinc	ppm	ASTM D5185m	1640	1243	1197	1209
Sulfur	ppm	ASTM D5185m		3990	3291	4122
Visc @ 40°C	cSt	ASTM D445	57.0	49.5	64.9	50.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0213296 **Received** : 22 May 2024
Lab Number : 06187930 **Tested** : 23 May 2024
Unique Number : 11044682 **Diagnosed** : 24 May 2024 - Sean Felton
Test Package : CONST (Additional Tests: PQ)

JRE - GREENSBORO
 411 SOUTH REGIONAL ROAD
 GREENSBORO, NC
 US 27409
 Contact: NICK GALLAHER
 NGALLAHER@JRENET.COM
 T: (336)668-2762
 F: (336)665-9556

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)