

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION ATTENTION

OKLAHOMA/102/EG - MOTOR GRADER 78.252 [OKLAHOMA^102^EG - MOTOR GRADER] Rear Left Drive Chain Case

MOBIL MOBILUBE HD PLUS 85W140 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.


FLUID CONDITION


The oil viscosity is lower than normal. This plus the additive levels indicates the addition of a different brand, or type of oil. Confirm oil type.

	···-/					
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0832395		
Sample Date		Client Info		14 May 2024		
Machine Age	hrs	Client Info		8182		
Oil Age	hrs	Client Info		8182		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				ATTENTION		
Iron	ppm	ASTM D5185m	>200	42		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m		3		
Lead	ppm	ASTM D5185m		<1		
Copper	ppm	ASTM D5185m		0		
Tin	ppm	ASTM D5185m		<1		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m		14		
Potassium	ppm	ASTM D5185m	>20	<1		
Water		WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	LIGHT		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium		ASTM D5185m		<1		
Boron	ppm ppm	ASTM D5185m		< 1		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		۰ <1		
Magnesium	ppm	ASTM D5185m		10		
Calcium	ppm	ASTM D5185m		2996		
Phosphorus	ppm	ASTM D5185m		975		
Zinc	ppm	ASTM D5185m		1182		
Sulfur	ppm	ASTM D5185m		6505		
Visc @ 40°C	cSt	ASTM D3103III	461	 0303 112 		
VISC @ 40 C	631	AG I IVI D440	401			

Report Id: SHEWIC [WUSCAR] 06188044 (Generated: 05/29/2024 11:17:08) Rev: 1

Submitted By: JASON GORGES





SHERWOOD CONSTRUCTION CO INC : WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0832395 Received 3219 WEST MAY ST : 22 May 2024 Lab Number : 06188044 Tested WICHITA, KS : 24 May 2024 Diagnosed : 24 May 2024 - Sean Felton US 67213 Contact: DOUG KING To discuss this sample report, contact Customer Service at 1-800-237-1369. doug.king@sherwood.net * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (316)617-3161 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: x:

Unique Number : 11044796 Test Package : CONST Certificate L2367

Report Id: SHEWIC [WUSCAR] 06188044 (Generated: 05/29/2024 11:17:10) Rev: 1

Laboratory

Sample No.

Submitted By: JASON GORGES Page 2 of 2