



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
VOLVO A35G 342035
Component
Drop Box
Fluid
MOBIL 75W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ML0001827	ML0000889	VCP407233
Sample Date		Client Info		17 May 2024	08 Mar 2024	03 Aug 2023
Machine Age	hrs	Client Info		9961	9143	8716
Oil Age	hrs	Client Info		818	427	500
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changed	Changed	Changed
Filter Changed		Client Info		Not Changed	None	N/A
Sample Status				NORMAL	NORMAL	SEVERE

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	183	18	▲ 1223
Chromium	ppm	ASTM D5185m	>20	2	0	▲ 14
Nickel	ppm	ASTM D5185m	>10	<1	0	4
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>30	3	0	9
Lead	ppm	ASTM D5185m	>30	0	0	<1
Copper	ppm	ASTM D5185m	>30	0	<1	4
Tin	ppm	ASTM D5185m	>20	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	9	<1	21
Potassium	ppm	ASTM D5185m	>20	1	0	3
Water		WC Method	>0.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<1	2	1
Boron	ppm	ASTM D5185m		246	223	178
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		1	0	27
Manganese	ppm	ASTM D5185m		2	0	10
Magnesium	ppm	ASTM D5185m		0	0	2
Calcium	ppm	ASTM D5185m		57	7	54
Phosphorus	ppm	ASTM D5185m		2410	2040	2036
Zinc	ppm	ASTM D5185m		25	12	136
Sulfur	ppm	ASTM D5185m		31152	26886	25056
Visc @ 40°C	cSt	ASTM D445		51.7	50.3	55.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ML0001827
Lab Number : 06188047
Unique Number : 11044799
Test Package : CONST

Received : 22 May 2024
Tested : 24 May 2024
Diagnosed : 24 May 2024 - Sean Felton

MCCLUNG-LOGAN EQUIPMENT CO - RICHMOND
 1345 MOUNTAIN ROAD
 GLEN ALLEN, VA
 US 23060
 Contact: KYLE RATLIFFE
 KRATLIFFE@MCCLUNG-LOGAN.COM
 T:
 F: (804)266-1611

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)