



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
PETERBILT 495169
Component
1 Diesel Engine
Fluid
DRYDENE 15W40 (--- GAL)

RECOMMENDATION

No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0017764	---	---
Sample Date		Client Info		08 May 2024	---	---
Machine Age	hrs	Client Info		76342	---	---
Oil Age	hrs	Client Info		40174	---	---
Filter Age	hrs	Client Info		40174	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>110	69	---	---
Chromium	ppm	ASTM D5185m	>4	4	---	---
Nickel	ppm	ASTM D5185m	>2	<1	---	---
Titanium	ppm	ASTM D5185m		3	---	---
Silver	ppm	ASTM D5185m	>2	<1	---	---
Aluminum	ppm	ASTM D5185m	>25	27	---	---
Lead	ppm	ASTM D5185m	>45	3	---	---
Copper	ppm	ASTM D5185m	>85	8	---	---
Tin	ppm	ASTM D5185m	>4	2	---	---
Vanadium	ppm	ASTM D5185m		<1	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION










Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	13	---	---
Potassium	ppm	ASTM D5185m	>20	74	---	---
Fuel		WC Method	>5	<1.0	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>3	0.5	---	---
Nitration	Abs/cm	*ASTM D7624	>20	11.9	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	28.3	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		4	---	---
Boron	ppm	ASTM D5185m		14	---	---
Barium	ppm	ASTM D5185m		0	---	---
Molybdenum	ppm	ASTM D5185m		58	---	---
Manganese	ppm	ASTM D5185m		2	---	---
Magnesium	ppm	ASTM D5185m		178	---	---
Calcium	ppm	ASTM D5185m		2374	---	---
Phosphorus	ppm	ASTM D5185m		1055	---	---
Zinc	ppm	ASTM D5185m		1288	---	---
Sulfur	ppm	ASTM D5185m		3901	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	24.7	---	---
Base Number (BN)	mg KOH/g	ASTM D2896		4.9	---	---
Visc @ 100°C	cSt	ASTM D445	14.4	13.1	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0017764
Lab Number : 06188380
Unique Number : 11045132
Test Package : FLEET

Received : 22 May 2024
Tested : 28 May 2024
Diagnosed : 28 May 2024 - Sean Felton

RTL PACLEASE - 7026 - Jacksonville
 718 Lane Ave N
 Jacksonville, FL
 US 32254

Contact: John Castleberry
 CastleberryJ@RushEnterprises.com

T: (904)559-4902

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: