

. . . . . . . . . .

----

## Machine Id **DFGS103469** Compone **Diesel Engine** DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0910957		
	Sample Date		Client Info		31 Mar 2024		
	Machine Age	hrs	Client Info		16133		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		6		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>4	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		3		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	<u>\</u> 25	4		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Fuel	ppm	WC Method		<1.0		
	Water		WC Method		NEG		
	Glycol		WC Method	20.2	NEG		
	Soot %	%	*ASTM D7844	>3	0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	8.6		
	Sulfation	Abs/.1mm	*ASTM D7415		21.7		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		372		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	100	92		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		450		
	Calcium	ppm	ASTM D5185m		1727		
	Phosphorus	ppm	ASTM D5185m	1150	1068		
	7		AOTH DELOF	1050	1000		

Zinc

Sulfur

Oxidation

Visc @ 100°C cSt

ppm

Base Number (BN) mg KOH/g ASTM D2896 8.5

ASTM D5185m 1350

ASTM D445 14.4

ppm ASTM D5185m 4250


Abs/.1mm \*ASTM D7414 >25

1296

3753 18.5

7.5

13.2



**DOLE FRESH FRUIT** Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WC0910957 Received PO BOX 725, ATTN: MAINTENANCE AND REPAIR : 22 May 2024 : 24 May 2024 Lab Number : 06188440 Tested NEW CASTLE, DE Diagnosed Unique Number : 11045192 : 24 May 2024 - Wes Davis US 19720 Test Package : FLEET Contact: LUIS LAPIERRE Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. luis.lapierre@dole.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (302)652-6344 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (302)652-6061

jā

Contact/Location: LUIS LAPIERRE - DOLWIL Page 2 of 2